

An in vitro evaluation of leakage of two Etch and Rinse and two Self-Etch adhesives
after thermocycling

Sabine Geerts*, Amandine Bolette, Laurence Seidel, Audrey Guéders

Geerts Sabine*, LSD, DMD, Professor, Division of Conservative and Adhesive Dentistry, Department of Dentistry, University of Liège, Liège, Belgium

Bolette Amandine, LSD, Division of Conservative and Adhesive Dentistry, Department of Dentistry, University of Liège, Liège, Belgium

Seidel Laurence, MSc, Department of Biostatistics, University of Liège, Liège, Belgium

Guéders Audrey, LSD, DMD, Division of Conservative and Adhesive Dentistry, Department of Dentistry, University of Liège, Liège, Belgium

* Reprints requests: CHU-Policlinique BRULL, Quai G. Kurth, Box 45, 4020 Liège, Belgium; phone number: 003242703131; fax number: 003242703110; e-mail address: sabine.geerts@ulg.ac.be

Abstract

Our experiment evaluated the microleakage in resin composite restorations bonded to dental tissues with different adhesive systems. 40 class V cavities were prepared on the facial and lingual surfaces of each tooth with coronal margins in enamel and apical margins in cementum (root dentin). The teeth were restored with Z100 resin composite bonded with different adhesive systems: Scotchbond™ Multipurpose (**SBMP**) a 3-step Etch and Rinse adhesive, Adper™ Scotchbond™ 1 XT (**SB1**) a 2-step Etch and Rinse adhesive, AdheSE® One (**ADSE-1**) a 1-step Self-Etch adhesive and AdheSE® (**ADSE**) a 2-step Self-Etch adhesive. Teeth were thermocycled and immersed in 50 % silver nitrate solution.

When both interfaces were considered, SBMP has exhibited significantly less microleakage than other adhesive systems (respectively for SB1, ADSE-1 and ADSE, $p = 0.0007$, $p < 0.0001$ and $p < 0.0001$). When enamel and dentin interfaces were evaluated separately: 1) for the Self-Etch adhesives, microleakage was found greater at enamel than at dentin interfaces (for ADSE, $p = 0.024$ and for ADSE-1, $p < 0.0001$); 2) for the Etch and Rinse adhesive systems, there was no significant difference between enamel and dentin interfaces; 3) SBMP was found significantly better than other adhesives both at enamel and dentin interfaces.

In our experiment Etch and Rinse adhesives remain better than Self-Etch adhesives at enamel interface. In addition, there was no statistical difference between 1-step (ADSE-1) and 2-step (ADSE) Self-Etch adhesives.

Introduction

Currently, resin composites are more often used for direct posterior teeth' restorations since many advances were made in adhesion and adhesives long-term performances. Adhesives are necessary to prevent leakage on resin composite restorations while dental composites are not able to bond to dental tissues. However, clinical microleakage remains the major cause for composite restorations failures implying post-operative sensibility, margin colorations, secondary decay or pulpal inflammation [1-5]. Therefore, manufacturers have proposed many different adhesives involving different adhesion strategies. These adhesive systems were well-described by Van Meerbeek et al. [6-8]: the Etch and Rinse (ER) adhesive systems (in three or two clinical steps), the Self-Etch (SE) adhesive systems (in two or one clinical step(s)) and the glass ionomer adhesives [6-9]. In their *in vitro* studies, several authors have reported different dental adhesive systems's bonding performance [10-24]. Therefore, results from thermocycling experiments have already pointed statistical differences between the ER adhesion strategy and the SE adhesion strategy [19, 25-27].

Therefore, the purpose of this study was to evaluate bonding performance of different dental adhesives after thermocycling: 2 ER adhesives (Scotchbond™ Multipurpose, **SBMP** -3M Espe AG, Seefeld, Germany- a 3-step ER adhesive and Adper™ Scotchbond™ 1 XT, **SB1** 3M Espe AG, Seefeld, Germany- a 2-step ER adhesive) and 2 SE adhesives (AdheSE®, **ADSE** –Ivoclar Vivadent AG, Schaan, Liechtenstein- a 2-step SE adhesive and AdheSE® One, **ADSE-1** –Ivoclar Vivadent AG, Schaan, Liechtenstein- a 1-step adhesive) were evaluated according to the microleakage that was observed.

Materials and Methods

Twenty recently extracted human third molars were randomly selected for this experiment. The teeth were stored in a refrigerated saline solution for a maximum of 3 months as recommended by the ISO norms (ISO. Guidance on testing of adhesion to tooth structure. International Organization for Standardization. TR 11405,1-4, Geneva, Switzerland, 1994). All patients and an appropriate Ethical Committee have approved the collection of extracted teeth. Two cavities were drilled on the facial and the lingual sides of each tooth. All the cavities (n = 40) were rectangular, standardized for dimensions and shape (h x w x l = 2 mm x 2 mm x 3 mm) and were prepared with a cylindrical diamond bur (diameter = 0.9 mm) at the coronal-radicular junction: the margins were butt-jointed, half in the enamel and half in the root dentin. After that, the apices were fixed in an autopolymerizing resin (Paladur™, Heraeus-Kulzer GmbH & Co. KG, Hanau, Germany).

The forty cavities were randomly assigned in 4 groups according to tested adhesive systems (Table 1):

- Scotchbond™ Multipurpose (SBMP) (3M ESPE AG, Dental products, Seefeld, Germany) a 3-step Etch and Rinse (ER) adhesive system;
- Adper™ Scotchbond™ 1 XT (SB1) (3M ESPE AG, Dental products, Seefeld, Germany) a 2-step Etch and Rinse (ER) adhesive system;
- AdhSE® (ADSE) (Ivoclar Vivadent AG, Schaan, Liechtenstein) a 2-step Self-Etch (SE) adhesive system ;
- AdhSE® One (ADSE-1) (Ivoclar Vivadent AG, Schaan, Liechtenstein) a 1-step Self-Etch (SE) adhesive system.

Table 1 – The different tested adhesive systems and their components

Adhesive systems

Name of the adhesives	Type of adhesives	Components
SBMP	ER, 3-step	Phosphoric acid (35%) Primer = HEMA, polyalkenoic acid copolymer, water Bonding = HEMA, Bis-GMA, amines, photo-initiator
SB1	ER, 2-step	Phosphoric acid (35%) Adhesive (primer + bonding) = dimethacrylates, HEMA, polyalkenoic acid copolymer, silanized silicium, alcohol, water, photo-initiator
ADSE	SE, 2-step	Primer = dimethacrylate, phosphonic acid acrylate, initiators, stabilizers Bonding = HEMA, dimethacrylate, silicon dioxide, Initiators, stabilizers
ADSE-1	SE, 1-step	Derivates of bis-acrylamide, water, alcohol, bis-metacrylamide dihydrogen phosphate, amino acid acrylamide, hydroxyl alkyl methacrylamide, alkyl sulfonic acid acrylamide, highly dispersed silicon dioxide, initiators, stabilizers and potassium fluoride

In this Table, the tested adhesives are displayed according to the adhesion's strategy and the type of adhesives: Etch and Rinse (ER) adhesive systems (SBMP and SB1) and Self-Etch adhesive systems (ADSE, ADSE-1).

SBMP = *Scotchbond™ Multi-purpose Plus (3M Espe AG, Dental products, Seefeld, Germany)*

SB1 = *Adper™ Scotchbond™ 1 XT (3M Espe AG, Dental products, Seefeld, Germany)*

ADSE = *AdheSE® (Ivoclar Vivadent AG, Schaan, Liechtenstein)*

ADSE-1 = *AdheSE® One (Ivoclar Vivadent AG, Schaan, Liechtenstein)*

All the tested adhesives were used according to the manufacturer's instructions. Immediately after bonding procedures, the cavities were filled with two oblique increments of a microhybrid composite (Z100™, 3M ESPE AG, Dental products, Seefeld, Germany). The photopolymerization was carried out for all materials with a halogen lamp (XL 3000, 3M ESPE AG, Dental products, Seefeld, Germany). Composite restorations were polished by means of diamond drills and disks (Hawe Neos Dental, Bioggio, Switzerland). The polishing was carried out under a spray of water. After that, all the specimens were immersed in a saline solution for twelve weeks (in a refrigerator at 5°C). Thereafter, the teeth were thermocycled for 800 cycles (5°C – 55°C) for 22 hours. After thermocycling, the teeth were immersed in a 50 % silver nitrate solution (for 6 hours) and in a 25 % vitamin C solution for 10 minutes (pH about 2) [25-26]. After immersion, three grooves (3 mm depth, 1 mm width) were drilled with a diamond bur in each restoration to obtain four surfaces of observation. The interfaces occurred between the teeth and the filling was described in our previous studies [25-26]. Briefly, the cylindrical diamond drill (0,9 mm-diameter) was placed perpendicular to the composite restoration. Three grooves 3 mm deep and 1 mm wide were cut on each restoration: one at the mesial margin, one at the distal margin and one right in the middle of the filling (Figure 1). These preparations yielded four evaluating surfaces for each composite restoration (Figure 2), for a total of 160 viewing surfaces for all tested adhesives. Each surface allowed one observation in enamel and one in dentin (lecture areas), for a total of 320 observations (160 in enamel and 160 in dentin).

Figure 1 – Diagram showing placement of the three grooves on each restoration, to provide eight observation areas




Figure 2 – Pictures of the composite restoration before and after grooves' preparation



Each section was examined by two-fold magnification by means of an optic microscope (Carl Zeiss, SAS, Oberkochen, Germany). Each tooth was observed twice by the same operator (blinded test).

Arbitrarily, the evaluation of leakage was made with a 6-point severity scale (Figure 3, Table 2) [25].

Figure 3 – Diagram showing the 6-point evaluation scale for leakage




Table 2: The 6-point severity scale to evaluate the microleakage

Scores	Signification
Score = 0	no leakage
Score = 1	leakage up to the enamel-dentin junction or a depth of 0.5 mm on the radicular wall
Score = 2	leakage up to the maximum half of the lateral wall (leakage depth \leq 1 mm)
Score = 3	leakage over half of the lateral wall (1 mm < leakage depth < 2 mm)
Score = 4	subtotal leakage on the whole of the lateral wall (leakage depth = 2 mm)
Score = 5	total leakage partly or entirely on the pulpal wall of the cavity (leakage depth > 2 mm)

We have postulated that higher scores of microleakage (scores 3, 4 and 5) after thermocycling would be responsible for clinical failure of the bonding (Figure 4).

Figure 4 – Picture showing a 2-score of microleakage (left) and 4-score of microleakage (right)



Statistical analysis

Results are expressed as means \pm standard deviations (\pm SDs). Microleakage scores were analyzed by means of generalized linear mixed models (GLMMs) assuming an ordinal logistic link function. Covariates in the model were (1) adhesive systems and (2) interface (enamel or dentin). The model also accounts for repeated measurements on the various teeth. All the results were considered to be significant at the 5% critical level ($p < 0.05$). Statistical calculations were made using the SAS 9.1 (version 8.2 for Windows) package.

Results

Microleakage mean score calculation for each tested adhesive system was analyzed by statistical model, which takes repeated evaluations into account (4 observations for each interface, enamel or dentin). Therefore, all the observed scores of microleakage for each adhesive at enamel or at dentin interface are not displayed.

The mean scores of microleakage for all tested adhesive systems are shown in the Table 3.

Table 3: Mean microleakage scores of the different tested adhesive systems

ER adhesive systems		SE adhesive systems	
	Mean microleakage scores (\pm SDs)		Mean microleakage scores (\pm SDs)
SBMP	0.30 \pm 0.49	ADSE	0.88 \pm 0.82
SB1	0.64 \pm 0.66	ADSE-1	0.84 \pm 0.72

In this Table, the tested adhesives are displayed according to the adhesion's strategy and type of adhesives: Etch and Rinse (ER) adhesive systems (SBMP and SB1) and Self-Etch adhesive systems (ADSE, ADSE-1).
SBMP, Scotchbond Multipurpose; SB1, Scotchbond 1 XT; ADSE, AdheSE; ADSE-1, AdheSE One.

In our study, SBMP was significantly different from other adhesives: SBMP has shown a lower mean score of microleakage (0.30 \pm 0.49) than other tested adhesives ($p = 0.0007$ for SB-1 and $p < 0.0001$ for the others tested adhesives).

The Table 4 reports the statistical comparison between the mean scores of microleakage of the 4 tested adhesives.

Table 4 : Statistical differences among the tested adhesives and level of significance (p)

	SBMP	SB1	ADSE	ADSE-1
SBMP	-			
SB1	0.0007	-		
ADSE	< 0.0001	0.0799	-	
ADSE-1	< 0.0001	0.072	0.96	-
SBMP, Scotchbond Multipurpose; SB1, Scotchbond 1 XT; ADSE, AdheSE; ADSE-1, AdheSE One.				

As seen in Table 4, there was no statistical difference between SB1 and ADSE ($p = 0.0799$), neither between SB1 and ADSE-1 ($p = 0.072$) nor between ADSE and ADSE-1 ($p = 0.96$).

The Table 5 shows the mean scores of microleakage for the 4 tested adhesives at enamel and dentin interfaces.

Table 5 : Mean microleakage scores of the tested adhesives at the enamel and dentin interfaces

Strategy of adhesion	Adhesive systems	Mean microleakage scores (\pm SD)		p
		Enamel	Dentin	
ER	SBMP	0.30 \pm 0.52	0.30 \pm 0.46	0.86
	SB1	0.68 \pm 0.73	0.60 \pm 0.59	0.79
SE	ADSE	1.03 \pm 0.70	0.73 \pm 0.91	0.024
	ADSE-1	1.20 \pm 0.65	1.48 \pm 0.60	< 0.0001
In this Table, the tested adhesives are displayed according to the adhesion's strategy and type of adhesives: Etch and Rinse (ER) adhesive systems (SBMP and SB1) and Self-Etch adhesive systems (ADSE, ADSE-1).				
SBMP, Scotchbond Multipurpose; SB1, Scotchbond 1 XT; ADSE, AdheSE; ADSE-1, AdheSE One.				

For ADSE and ADSE-1, the mean scores of microleakage were significantly lower at dentin than at enamel interfaces.

Discussion

For the past few years, composite has become current restorative material and today it often replaces from amalgam restorations in posterior teeth [28-31]. Nevertheless, restorative composite is not able to bond to dental tissues. Therefore, the use of an adhesive system is always required. As result of numerous advances in adhesive technology and adhesion knowledge, there are many adhesive systems available on the market. To avoid confusing and incorrect uses of the adhesives, Professor Bart Van Meerbeek has proposed a classification according to different adhesion strategies and adhesives: the Etch and Rinse (ER) adhesive systems, the Self-Etch (SE) adhesive systems and the glass ionomer adhesive systems [6, 7, 32]. The ER adhesives always involve the use of phosphoric acid, which permits demineralization of the dental tissues and after rinsing, a complete elimination of the smear layer. Therefore, in the course of the ER adhesion strategy, the adhesive resin (bonding) is applied in a different clinical step: the demineralization and the hybridization of dental substrate appear consecutively. On the contrary, with the SE adhesives the demineralization and the impregnation of the adhesive into the enamel-dentin support appear simultaneously. The demineralization process results from the acidic monomers, which are components of the adhesive system. Therefore, the SE adhesive must not be rinsed. There are currently 4 different types of SE adhesives, which are indexed according to their pH value: the ultra-mild SE (pH about 2.5), the mild SE (pH about 2), the intermediary strong SE (pH about 1.5) and the strong SE (pH < 1) [6-8, 32]. On the enamel, for both ER and SE adhesive systems, bonding to the tissue is essentially micro-mechanical. On the dentin, for the ER adhesives, the mechanisms of adhesion are mainly micro-mechanical because the phosphoric acid is a very strong acid (pH about 0.5). Phosphoric acid completely dissolves the mineral and so, the collagen fibers are totally exposed after etching. For the SE adhesives, the adhesion to the dentin is both micro-mechanical and chemical [6- 8]: the self-etch monomers are often less acidic than phosphoric acid and then some minerals remain

attached to the collagen fibers, permitting chemical links between dental substrate and functional groups of the adhesive monomers.

Laboratory experiments have permitted comparison between different bonding materials and have pointed statistical differences between different adhesive systems [10-24]. Currently, a lot of studies and reviews agree about the best performances of the ER adhesive systems at the enamel and also at the dentin interface for some 3-step adhesives [11, 16, 19, 32-37]. Concerning dentin interface, several authors admit that some SE adhesives, in particular mild and ultra-mild, are able to create chemical bonds with hydroxyapatite crystals within the dentinal tissue [7, 8, 32, 36, 37, 40-42]. Nevertheless, some authors suggest that these mild and ultra-mild SE adhesives have poor adhesion capacity to the enamel tissue: so, they recommend the use of phosphoric acid on the enamel surface before applying the SE adhesive [32, 34, 37, 43-45].

Currently, *in vitro* microleakage [11, 19] and mechanical tests [16, 35] often show the superiority of the 3-step ER adhesives. For several authors, these adhesive systems are always the “gold standard” [6, 7, 32, 36-38], in particular the Optibond™ FL (*Kerr, European Union Representative, Scafati (SA), Italy*) [5, 7, 39] and/or the Scotchbond™ Multi-purpose Plus (SBMP) (*3M Espe AG, Seefeld, Germany*) [5, 36, 38]. The results of our study are in agreement with the data from the literature: in our experiment, SBMP has shown the best results in terms of microleakage.

Nevertheless, for some authors, 2-step mild and ultra-mild SE adhesives can give comparable results than those obtained by some 2-step ER adhesives and also, by some 3-step ER adhesive systems [6-10, 32, 34, 36, 37]. In fact, our results have shown that ADSE (2-step SE) and SB1 (2-step ER) have statistically comparable mean scores of microleakage.

Concerning the 1-step SE adhesives, some *in vitro* studies have shown their poor performances [7, 34, 46]. Our results don't confirm this fact: there is no statistical difference

between the mean scores of microleakage of ADSE (a 2-step SE) and its simplified clinical version, ADSE-1 (a 1-step SE). In addition, the mean scores of microleakage of these two mild SE adhesives (pH about 2) are lower at the dentin interface than at the enamel interface. These observations agree with data from the literature: ADSE and ADSE-1 are not efficient to create a sufficient micro-mechanical retention at the enamel surface [6, 7, 16, 34, 45]. Nevertheless, at the dentin surface, these mild SE adhesives are able to create a partial demineralization of this tissue to allow a micro-mechanical adhesion [6, 7]. In addition, some functional monomers of these SE adhesives might form chemical bonds with the calcium of the residual hydroxyapatite crystals linked to the collagen fibers [7, 32, 40-42]. The chemical bonds between ADSE' functional monomers haven't been clearly identified yet, but this adhesive has given good results in our study, like in the study of Bradna et al. [10].

Conclusion

In this study, confirming previous studies about marginal microleakage of the ER adhesive systems, SBMP, a 3-step ER adhesive, has significantly less microleakage comparing to other adhesive systems and can be considered like a reference adhesive. The parameters of this experiment (hydrolysis and thermocycling) have shown the good *in vitro* behaviour of SBMP. Therefore, we can expect that this ER adhesive will be clinically satisfying. In fact, this adhesive has been widely used for many years and their performances have seemed good. The 2-step ER adhesive that was tested in our study has shown a significantly greater mean score of microleakage than the tested 3-step ER adhesive system, but all the tested adhesives showed minimal leakage.

In the limits of our study, ADSE and ADSE-1 show poor microleakage, particularly on the dentin. Nevertheless, we suggest these mild SE adhesives can be used when the margins of the cavity are located on dentin and/or using phosphoric acid only on the enamel margin in order to optimize micro-mechanical interlocking.

References

1. Bullard RH, Leinfelder KF & Russell CM. Effect of coefficient of thermal expansion on microleakage. *Journal of American Dental Association* 1988; 116: 871-874.
2. Crim GA & Garcia-Godoy F. Microleakage: the effect of storage and cycling duration. *Journal of Prosthetic Dentistry* 1987; 57(5): 574-576.
3. Pioch T, Staehle HJ, Duschner H, Tavernier B & Colon P. Effect of dentin adhesives on the enamel-dentin/composite interfacial microleakage. *American Journal of Dentistry* 2001; 14: 252-258.
4. Rees JS, O'Dougherty D & Pullin R. The stress reducing capacity of unfilled resin in a class V cavity. *Journal of Oral Rehabilitation* 1999; 26: 422-427.
5. Van Meerbeek B, Yoshida Y, Lambrechts P, Vanherle G, Duke ES, Eick JD & Robinson SJ. A TEM study of two water-based adhesive systems bonded to dry and wet dentin. *Journal of Dental Research* 1998; 77(1): 50-59.
6. Van Meerbeek B, Vargas M, Inoue S, Yoshida Y, Peumans M, Lambrechts P & Vanherle G. Adhesives and cements to promote preservation dentistry. *Operative Dentistry* 2001; (Supplement 6): 119-144.
7. Van Meerbeek B, De Munck J, Yoshida Y, Inoue S, Vargas M, Vijay P, Van Landuyt K, Lambrechts P & Vanherle G. Buonocore Memorial Lecture – Adhesion to enamel and dentin: current status and future challenges. *Operative Dentistry* 2003; 28(3): 215-235.
8. Van Meerbeek B, Yoshihara K, Yoshida Y, Mine A, De Munck J & Van Landuyt KL. State of the art of self-etch adhesives. *Dental Materials* 2011; 27(1): 17-28.
9. Pashley DH, Tay FR, Breschi L, Tjäderhane L, Carvalho RM, Carrilho M & Tezvergil-Mutluay A. State of the art of etch-and-rinse adhesives. *Dental Materials* 2011; 27(1): 1-16.
10. Bradna P, Vrbova R, Dudek M, Roubickova A & Housova D. Comparison of bonding performance of self-etching and etch-and-rinse adhesives on human dentin using reliability analysis. *Journal of Adhesive Dentistry* 2008; 10(6): 423-429.

11. Ernsta CP, Kötter T, Victor A, Canbek K, Brandenbusch M & Willershausen B. Marginal integrity of self- and total-etching adhesives in two different application protocols. *Journal of Adhesive Dentistry* 2004; 6(1): 25-32.
12. Ferrari M, Cagidiaco MC, Kugel G & Davidson CL. Dentin infiltration by three adhesive systems in clinical and laboratory conditions. *American Journal of Dentistry* 1996; 9: 240-244.
13. Fortin D, Swift EJ Jr, Denehy GE & Reinhardt JW. Bond strength and microleakage of current dentin adhesives. *Dental Materials* 1994; 10(4): 253-258.
14. Frankenberger R, Perdigao J, Rosa BT & Lopes M. "No-bottle" versus "multi-bottle" dentin adhesives- a microtensile bond strength and morphological study. *Dental Materials* 2001; 17: 373-380.
15. Grégoire G, Joniot S, Guignes P & Millas A. Dentin permeability: self-etching and one-bottle dentin bonding systems. *Journal of Prosthetic Dentistry* 2003; 90(1): 42-49.
16. Hara AT, Amaral CM, Pimenta LAF & Sinhoreti MAC. Shear bond strength of hydrophilic adhesive systems to enamel. *American Journal of Dentistry* 1999; 12: 181-184.
17. Holtan JR, Nystrom GP, Olin PS, Phelps RA, Phillips JJ & Douglas WH. Bond strength of six dentinal adhesives. *Journal of Dentistry* 1994; 22: 92-96.
18. Inoue S, Vargas MA, Abe Y, Yoshida Y, Lambrechts P, Vanherle G, Sano H & Van Meerbeek B. Microtensile bond strength of eleven contemporary adhesives to dentin. *Journal of Adhesive Dentistry* 2001; 3: 237-245.
19. Owens BM & Johnson WW. Effect of insertion technique and adhesive system on microleakage of class V resin composite restorations. *Journal of Adhesive Dentistry* 2005; 7: 303-308.
20. Pilo R & Ben-Amar A. Comparison of micro-leakage for three one-bottle and three multiple-step dentin bonding agents. *Journal of Prosthetic Dentistry* 1999; 82: 209-213.
21. Swift EJ, Triolo PT, Barkmeier WW, Bird JL & Bounds SJ. Effect of low viscosity resins on the performance of dental adhesives. *American Journal of Dentistry* 1996; 9(3): 100-104.

22. Van Meerbeek B, Peumans M, Verschueren M, Gladys S, Braem M, Lambrechts P & Vanherle G. Clinical status of ten dentin adhesive systems. *Journal of Dental Research* 1994; 73: 1690-1702.
23. Van Meerbeek B, De Munck J, Mattar D, Van Landuyt K & Lambrechts P. Microtensile bond strengths of an Etch&Rinse and Self-Etch adhesive to enamel and dentin as a function of surface treatment. *Operative Dentistry* 2003; 28(5): 647-660.
24. Vargas MA & Swift EJ. Microleakage of resin composites with wet versus dry bonding. *American Journal of Dentistry* 1994; 7(4): 187-189.
25. Cao L, Geerts S, Guéders A, Albert A, Seidel L & Charpentier J. Experimental comparison of cavity sealing ability of five dental adhesive systems after thermocycling. *Journal of Adhesive Dentistry* 2003; 5: 139-144.
26. Guéders A, Charpentier J, Albert A & Geerts S. Microleakage after thermocycling of 4 etch and rinse and three self-etch adhesives with and without a flowable composite lining. *Operative Dentistry* 2006; 31(4): 450-455.
27. Rosales-Leal J. Microleakage of class V restorations placed with etch-and-rinse and self-etching adhesives before and after thermocycling. *Journal of Adhesive Dentistry* 2007 (Supplement 9): 255-259.
28. Lopes GC, Vieira LC & Araujo E. Direct composite resin restorations: a review of some clinical procedures to achieve predictable results in posterior teeth. *Journal of Esthetic and Restorative Dentistry* 2004; 16: 19-31.
29. Lopes GC & Oliveira GM. Direct composite resin restorations in posterior teeth. *Compendium of Continuing Education in Dentistry* 2006; 27: 572-579.
30. Javaheri DS. Posterior direct composites: clinical protocol. *Dentistry Today* 2007; 26: 94, 96-97.
31. Mackenzie L, Shortall AC & Burke FJ. Direct posterior composites: a practical guide. *Dental Update* 2009; 36: 71-72, 74-76, 79-80.

32. Van Meerbeek B, Peumans M, Poitevin A, Mine A, Van Ende A, Neves A & De Munck J. Relationship between bond-strength tests and clinical outcomes. *Dental Materials* 2010; 26: e100-e121.
33. Almeida KG, Scheibe KG, Oliveira AE, Alves CM & Costa JF. Influence of human and bovine substrate on the microleakage of two adhesives systems. *Journal of Applied Oral Sciences* 2009; 17(2): 92-96.
34. Apap M. Adhésifs auto-mordançants: un bon plan ? *L'Information Dentaire* 2007 ; 43 : 2804-2816.
35. Degrange M & Lapostolle B. L'expérience des batailles des adhésifs. *L'Information Dentaire* 2007; 89: 112-118.
36. Ernst C-P. Options for dentin bonding. *Journal of Esthetic and Restorative Dentistry* 2006; 18 (2): 61-67.
37. Peumans M, De Munck J, Van Landuyt K, Lambrechts P & Van Meerbeek B. Three-year clinical effectiveness of a two-step self-etch adhesive in cervical lesions. *European Journal of Oral Sciences* 2005; 113: 512-518.
38. Brandt PD, de Wet FA & du Preez IC. Self-etching bonding systems: in-vitro micro-leakage evaluation. *Journal of the Dental Association* 2006; 61(1): 248, 250-1.
39. Asmussen E & Peutzfeldt A. Short- and long-term bonding efficacy of a self-etch adhesive systems. *Operative Dentistry* 2007; 32: 73-78.
40. Fukegawa D, Hayakawa S, Yoshida Y, Suzuki K, Ozaka A & Van Meerbeek B. Chemical interaction of phosphoric acid ester with hydroxyapatite. *Journal of Dental Research* 2006; 85(10): 941-944.
41. Nagakane K, Yoshida Y, Hirata I, Fukuda R, Nakayama Y, Shirai K, Ogawa T, Suzuki K, Van Meerbeek B & Okazaki M. Analysis of chemical interaction of 4-MET with hydroxyapatite using XPS. *Dental Materials Journal* 2006; 25(4): 645-649.
42. Yoshida Y, Nagakane K, Fukuda R, Nakayama Y, Okazaki M, Shintani H, Inoue S, Tagawa Y, Suzuki K, De Munck J & Van Meerbeek B. Comparative study on adhesive performance of functional monomers. *Journal of Dental Research* 2004; 83(6): 454-458.

43. Degrange M. Les systèmes adhésifs amélo-dentinaires. *Réalités Cliniques* 2005; 16(4): 327-348.
44. Perdigao J, Monteiro P & Gomes G. In vitro enamel sealing of self-etch adhesives. *Quintessence International* 2009; 40(3): 225-233.
45. Van Landuyt KL, Kanumilli P, De Munck J, Peumans M, Lambrechts P & Van Meerbeek B. Bond strength of a mild self-etch adhesive with and without prior acid-etching. *Journal of Dentistry* 2006; 34(1): 77-85.
46. Hosaka K, Tagami J, Nishitani Y, Yoshiyama M, Carrilho M, Tay FR, Agee KA & Pashley DH. Effect of wet versus dry testing on the mechanical properties of hydrophilic self-etching primer polymers. *European Journal of Oral Sciences* 2007; 115: 239-245.