

Catechols as versatile platforms in polymer chemistry

Emilie Faure,^a Céline Falentin-Daudré,^a Christine Jérôme,^a Joël Lykawa,^{b c d} David Fournier,^{b c}
Patrice Woisel*,^{b c d e} Christophe Detrembleur*^a

^a Center for Education and Research on Macromolecules (CERM), Department of Chemistry,
University of Liege, Bldg B6a, Sart-Tilman, 4000 Liege, Belgium

^b Université Lille Nord de France, F-59000 Lille, France

^c USTL, Unité des Matériaux Et Transformations (UMET, UMR 8207), Equipe Ingénierie des
Systèmes polymères, F-59655 Villeneuve d'Ascq Cedex, France.

^d Fédération Biomatériaux et Dispositifs Médicaux Fonctionnalisés (BDMF/FED 4123)

^e ENSCL, F-59655 Villeneuve d'Ascq, France

Abstract: Catechols represent an important and versatile building block for the design of mussel-inspired synthetic adhesives and coatings. Indeed, their ability to establish large panoply of interactions with both organic and inorganic substrates has promoted catechol as a universal anchor for surface modifications. In addition to its pivotal role in adhesive interfaces, the catechol unit recently emerged as a powerful building block for the preparation of a large range of polymeric materials with intriguing structures and fascinating properties. The importance of catechols as efficient anchoring groups has been highlighted in recent excellent reviews partly dedicated to the characterization of their adhesive mechanisms onto

surfaces and to their applications. The aim of this paper is to review for the first time the main synthetic approaches developed for the design of novel catechol-based polymer materials. We will also highlight the importance of these groups as versatile platforms for further functionalization of the macromolecular structures, but also surfaces. This will be illustrated by briefly discussing some advanced applications developed from these catechol-modified polymers. The review is organized according to the chemical structure of the functionalized catechol polymers. Chapter 1 discusses polymers bearing catechols embedded into the polymer main chain. Chapter 2 focuses on the attachment of catechol moieties as pendant groups and Chapter 3 describes the different approaches for incorporation of the catechol unit at the extremity of well-defined polymers.

Keywords

Catechol derivatives, functional polymers, architectures

Table of contents

1. Introduction
2. Main chain precursors
 - 2.1. Autopolymerization in aerated basic solutions.
 - 2.1.1. General process and initial developments.
 - 2.1.2. Poly(catecholamines) – platforms for the design of advanced (nano)hybrids.
 - 2.1.2.1. Poly(catecholamines): reducers of metal salts and other oxides.
 - 2.1.2.2. Poly(catecholamines) as templates for the formation of minerals.
 - 2.1.2.3. Poly(catecholamines) as anchoring layers for polymer brushes and other (bio)macromolecules.
 - 2.2. Polymerization of catechols catalyzed by enzymes.
3. Side chain precursors
 - 3.1. Polymerization of catechol based vinyl monomers.
 - 3.1.1. Starting from protected monomers.
 - 3.1.2. Starting from unprotected monomers.
 - 3.2. Peptide synthesis of DOPA derivatives.
 - 3.2.1. By solid phase peptide synthesis.
 - 3.2.2. By ring-opening polymerization of α -amino acid *N*-carboxyanhydrides (NCAs).
 - 3.3. Chemical ligation of catechol derivatives onto preformed (bio)polymers.
 - 3.3.1. Grafting of catecholamines onto activated carboxylic acid functionalized polymers.
 - 3.3.2. Grafting of catecholamines onto hydroxyl functionalized polymers.
 - 3.3.3. Grafting of catecholbearing a carboxylic acid group onto amino functionalized polymers.

- 3.3.4. Electrochemical grafting of catecholunits onto amino functionalized polymers.
- 3.4. Enzymatic derivatization of (bio)polymers bearing tyrosine moieties.
- 4. End chain precursors
 - 4.1. Grafting of catechol unit(s) onto chain-ends by chemical ligation.
 - 4.2. Elaboration of catechol end-functionalized polymers via controlled/living and electrochemical polymerizations techniques.
- 5. Conclusions

List of abbreviations

AB	TEM
AFM	antibacterial
AIBN	atomic force microscopy
ATRP	2,2'-azobisisobutyronitrile
BIBB	atom transfer radical polymerization
CNTs	2- bromoisobutyryl bromide
CRP	carbon nanotubes
CuAAC	controlled radical polymerization
DLS	copper-catalyzed azide-alkyne 1,3-dipolar cycloaddition
DMAEMA ⁺	dynamic light scattering
DMAP	(2-(methacryloxy)ethyl) trimethylammonium chloride
DOPA	4-dimethylaminopyridine
EDC	3,4-dihydroxyphenyl-L-alanine
H ₂ O ₂	ethyl(dimethylaminopropyl) carbodiimide
HBTU	hydrogen peroxide
	<i>O</i> -(benzotriazol-1-yl)- <i>N,N,N',N'</i> -tetramethyluronium
HEMA	hexafluorophosphate
HOBt	2-hydroxyethyl methacrylate
HRP	1-hydroxybenzotriazole hydrate
LbL	horseradish peroxidase
Mefp	layer-by-layer
MMT	mytilusedulis foot protein
NCA	Na ⁺ -montmorillonite
NHS	α -amino acid <i>N</i> -carboxyanhydride
NPC	<i>N</i> -hydroxysuccinimide
PAA	<i>p</i> -nitrophenyl-chloroformate
PAH	poly(acrylic acid)
PCL	poly(allylamine hydrochloride)
PDMS	poly(ϵ -caprolactone)
PEG	poly(dimethylsiloxane)
PEI	poly(ethylene glycol)
PNIPAM	poly(ethylenimine)
PolyDp	poly(<i>N</i> -isopropylacrylamide)
PSS	poly(dopamine)
PTFE	poly(styrene sulfonate)
RAFT	poly(tetrafluoroethylene)
ROMP	reversible addition-fragmentation chain transfer polymerization
ROP	ring-opening metathesis polymerization
SLS	ring opening polymerization
SBP	static light scattering
SEM	soybean peroxidase
Sn(Oct) ₂	scanning electron microscopy
TEA	tin(II) octanoate

triethylamine
transmission
electron
microscopy
TsT
V-501
XPS

Trichloro-*s*-triazine
4,4'-azobis(4-cyanopentanoic acid)
x-ray photoelectron spectroscopy

1. Introduction

Catechols occur naturally in fruits and vegetables but in poisons, insects and teas as well. They are small molecules widely used for synthesis in food, pharmaceuticals or agrochemical ingredients, but also as stabilizing additives. For instance, *tert*-butylcatechol is largely employed as a polymerization inhibitor.[1] In organic chemistry, catechol and its derivatives have widely attracted scientists since decades. Indeed, they can act as antioxidant agents, as chelating agents in coordination chemistry or trap radicals to cite only few (Fig. 1).




Fig. 1. Main chemical properties of catechols.

In 1981, catechols have been identified by Waite and coworkers to be responsible for the versatile adhesion of mussels in the most inhospitable regions under very harsh and wet conditions.[2] This important discovery led to deeply studying the exact structure of the proteins responsible for the adhesion of mussels and their action mode.[3-6] The

posttranslationally modified amino acid, 3,4-dihydroxyphenyl-L-alanine (DOPA; **2**, Fig. 2), has been determined as the main element required for this moisture-resistant adhesion.[4] Proteins found in the mussel adhesive plaque, Mefp for *Mytilusedulis* foot protein, were largely characterized and six of them were identified to present a DOPA content ranging from 3 mole % (Mefp-2) to 30 mole % (Mefp-5).[5, 7] Evidences of its role in strong interactions with either organic or inorganic surfaces have been afforded by Atomic Force Microscopy (AFM) on both small polymer chains containing catechol end groups[8] and Mefps[9]. Specific adhesion mechanism of these small molecules to a large panel of surfaces is still not completely understood. It has been studied for many years and several proposals of interaction modes can be found in the literature. These have been reviewed elsewhere[10] and seem to be substrate dependent. However in all cases, covalent or strong non-covalent interactions (hydrogen bonds or π - π stacking interactions for instances) can be found between catechol groups and inorganic substrates such as mica[11] for example. As far as metal oxides are concerned, catechol groups are assumed to form bidentate bonding with the metal surface.[12, 13]




Fig. 2. Catechol and some derivatives.

This amazing adhesion under wet conditions combined with the intrinsic properties of catechols cited here above (antioxidant, ligation ability ...) have opened the door to the design of new (multi)functional platforms based on catechols. This review describes the state-of-the-art research in the synthesis of (bio)macromolecules bearing catechols that are used as versatile platforms for the design of adherent materials, multifunctional materials and inorganic/polymer hybrids. Numerous scientific groups have worked worldwide on this topic since almost fifteen years. These works will be further detailed in the following sections. Briefly, catechol functions can be incorporated into macromolecules as main, side and end-chain groups by employing various synthetic pathways. The successfully employed strategies include i) either the oxidative[14] or enzymatic[15] polymerization of functional catechols; ii) the polymerization of monomers bearing catechol groups protected or not (radical polymerization[16] or peptide synthesis[17]); iii) the controlled/living polymerization of synthetic monomers in the presence of catechol based initiators (ATRP,[18] ROMP[19] ...) or chain transfer agents (RAFT[20]). The point that will be stressed on in this review concerns the final architecture of the different macromolecules obtained from these different synthetic approaches (Fig. 3). We will also emphasize how the reactivity of the catechol functional groups can be nicely exploited for further polymer derivatizations and for the development of advanced applications.




Fig. 3. Catechol based building blocks for macromolecular engineering.

2. Main chain precursors

Molecules bearing catechols are easily converted into highly reactive quinones either by a strong oxidant agent such as NaIO_4 [21] or an enzyme (horseradish peroxidase combined with hydrogen peroxide, HRP/ H_2O_2 , for instance[15]), but also by an aerated aqueous solution at neutral to alkaline pH.[22] In some conditions that will be detailed below, self-polymerization of some of these oxidized products is observed, leading to polymers that are of prime importance in the field of surface modifications. These oxidative polymerizations result in the formation of uncontrolled cross-linked films composed of a mixture of cross-linked products bearing mostly catechol and quinone groups that can be exploited for further derivatizations as it will be illustrated in the next sections.

2.1. Autopolymerization in aerated basic solutions.

2.1.1. *General process and initial developments.*

Autopolymerization of catecholamines in aerated basic conditions was first demonstrated by Messersmith *et al.* for dopamine (**3**, Fig. 2) in a Tris buffered dopamine solution at pH 8.5.[14] When this polymerization occurs in the presence of substrates, an adherent poly(dopamine) (polyDp) film is *in situ* deposited on the surface after 24 hours of immersion (Fig. 4). Film thickness increases with the immersion time as shown on Fig.5 (A) where a plateau is obtained after 24 hours.[14] Final polyDp thickness also increases with the polymerization temperature.[23] Both organic and inorganic surfaces were well covered, including poly(tetrafluoroethylene) (PTFE), known for its antiadhesion properties (Fig. 5 (B)).[14]




Fig. 4. Poly(dopamine) (polyDp) network adapted from Messersmith *et al.*[14]




Fig. 5. Thickness evolution of poly(dopamine) (polyDp) coating on Si as measured by AFM of patterned surfaces (A), X-ray Photoelectron Spectroscopy (XPS) characterizations of several polyDp coated surfaces (B).[14] The bar graph represents the intensity of characteristic substrate signal before (hatched) and after (solid) coating with polyDp. “N.A.” means that XPS signals of the substrates were indistinguishable from the polyDp signal. The blue circles represent the nitrogen/carbon ratio after polydopamine coating.

From a mechanistic point of view, the polyDp network (Fig. 4) is presumably formed by Schiff base formation and/or by Michael type addition involving quinone groups of oxidized dopamine with its primary amino group.[8, 24, 25] Up to now, the exact structure of polyDp is still lacking in the literature but some proposals can be found in publications. As established spectrophotometrically by Linert and coworkers, dopamine oxidation leads to dopaminochrome (**10**, Fig. 6) following a multistep reaction pathway.[22] This molecule can then self-polymerize and produce polymers that are usually complex networks with free catechol groups available for further chemical reactions (**11** and **12**, Fig. 6). These catechol groups are responsible for the strong adhesion of the polymer network to any kind of surfaces, both organic (polysulfone,[26, 27] polyethersulfone,[28] polyethylene,[29] polypyrrole,[30] hydrophobic/superhydrophobic polymers, [31-33] silanes[34-37] and even yeast cells[38] or raw cherry tomato[39]) and inorganic (clays,[40] iron-based nanoparticles,[41, 42] gold,[43] SiO₂[44-47] and others[48-52]). Melanin formation follows a similar process and also produces such complex systems.[53]




Fig. 6. Mechanistic scheme for the formation of polyDp (**11** and **12**) by self-polymerization of dopamine.[43, 51, 54]

The ability of PolyDp to adhere onto various substrates has been largely exploited to promote cells adhesion on several surfaces such as glass, polystyrene, poly(dimethylsiloxane) (PDMS) and even PTFE.[55-58] Very recently, Jiang and coworkers managed to pattern PEG-coated surfaces with polyDp using microcontact printing (μ CP) and PDMS stamps (Fig. 7) which were further exploited to spatially control the anchoring of mammalian cells.[58]




Fig. 7. Strategy for cells patterning using polyDp coating (scale bar is 100 μm).[58]

The substrates can also play the role of sacrificial templates that are removed after polyDp formation in order to form stable polyDp capsules[59-65] that can be loaded with hydrophobic drugs such as anticancer agent (thiocoraline).[66] As no drug leakage was observed after template removal, these new drug carriers have opened the door to potential applications in biotechnology and drug delivery systems for instances. More particularly, Zhou and coworkers have demonstrated pH stability for such microcapsules with outstanding unidirectional loading of rhodamine 6G (Rh6G) in some solvents.[60] Indeed, the polyDp capsules are almost impermeable to Rh6G in ethanol while the inverse is observed in aqueous solution with uptake rates that depend on pH (increased at high pH). The loading in aqueous solution is driven by the high osmotic outside pressure and gradient chemical potential. At a low pH, the amino groups of polyDp are protonated and charge repulsion between them and the positively charged dye is responsible for the low loading efficiency. At high pH, the catechols become negatively charged favoring the diffusion of the dye inside the capsules.

Beside the intrinsic properties of polyDp, the presence of residual quinone groups onto the polymer backbone allows for further modifications with thiol compounds (alkanethiol, thiol-terminated methoxy-poly(ethylene glycol), thiolated hyaluronic acid) [54, 67] and nitrogen derivatives (amine-terminated methoxy-poly(ethylene glycol), imidazoles)[68-70] leading to the formation of new materials with different structures and properties (Fig. 8).




Fig. 8. Possible reaction pathways of oxidized catechols with amines, thiols or imidazoles where R' stands for a polymeric or peptidic backbone.

These pioneering works have opened up wide possibilities for the preparation of adherent poly(catecholamines) based coatings on any kind of substrates [14, 71]. Their applications in the biomedical field has been the topic of a recent review [72]. Although the catechol groups are responsible for the strong adhesion of the coatings to the substrates, their high reactivity towards various reagents is also exploited for further derivatization to provide various surface functionalities (Fig. 9), as it will be discussed in the following sections.




Fig. 9. Polydopamine coating and further derivatizations.

2.1.2. Poly(catecholamines) – platforms for the design of advanced (nano)hybrids.

2.1.2.1. Poly(catecholamines): reducers of metal salts and other oxides.

Catechol groups of polyDp can act as strong reducing agents for graphene oxide[54, 73, 74] and metal salts for the production of metal nanoparticles[75, 76] (Fig. 9, pathway A). For instance, Xinet *al.* have obtained carbon nanotubes (CNTs) coated with gold nanoparticles in a two steps procedure.[77] CNTs were first coated by polyDp by immersion in a buffered dopamine solution, followed by dipping into HAuCl_4 aqueous solution. Nanometric gold particles (20-30 nm size) were obtained by reduction of Au^{3+} by catechols of polyDp without the need of any other chemical reagent (Fig. 10).




Fig. 10. Transmission Electron Microscopy (TEM) images of carbon nanotubes coated with polyDp (A,C) and carbon nanotubes coated with polyDp and Au nanoparticles (B, D).[77] Scale bars are 200 nm (A), 350 nm (B), 10 nm (C) and 50 nm (D).

Silver nanoparticles have also been immobilized in a similar way on various polyDp coated substrates [78-82] to obtain final antibacterial (AB) properties [83, 84]. Such silver nanoparticles can also be elaborated in solution by mixing dopamine and AgNO_3 under alkaline conditions leading to a bright yellow solution of Ag^0 nanoparticles stabilized with a polyDp coating. [85] This material was then exploited for the fast and sensitive colorimetric detection of Cu^{2+} ions. Indeed, in the presence of Cu^{2+} , the initially bright yellow polyDp/ Ag^0 assembly aggregated with the formation of a dark brown suspension (Fig. 11).




Fig. 11. Mechanism of colorimetric determination of Cu^{2+} with silver/dopamine nanoparticles. *Reproduced with permission from ref [85]. Copyright 2011 The Royal Society of Chemistry.*

2.1.2.2. Poly(catecholamines) as templates for the formation of minerals.

Based on these remarkable binding properties towards various metal ions[86, 87], different research groups have also used polyDp coatings as templates for the formation of hydroxyapatite by co-precipitation of calcium and phosphate ions (Fig. 12).[88-90] The hydroxyapatite formation can be carried out on various kinds of surfaces such as CNTs[88, 90] or polymeric substrates (porous cellulose, polyester, polytetrafluoroethylene for instances)[89] to convert them into scaffolds for bone tissue regeneration and implantation.

Such stabilizing effect of the catechols towards ionic species has also been exploited by Park *et al.* for the mineralization of CaCO_3 vaterite crystals which were further transformed into bone hydroxyapatite minerals in a simulated body fluid.[91-93] CaCO_3 microspheres

were prepared by mixing CaCl_2 and Na_2CO_3 with dopamine[91, 92] or by bubbling CO_2 in an aqueous mixture of CaCl_2 , NH_4OH and dopamine[93].




Fig. 12. A) Formation of calcium phosphate crystals on polyDp coatings, B) Scanning Electron Microscopy (SEM) images of polyester fibers (1 and 2) and PTFE membrane (3 and 4) without and with hydroxyapatites.[89]

2.1.2.3. Poly(catecholamines) as anchoring layers for polymer brushes and other (bio)macromolecules.

PolyDp coating were also exploited to graft (i) an ATRP (Atom Transfer Radical Polymerization) initiator for controlled radical polymerization[94-97] to generate well-defined polymer brushes on various surfaces via a “grafting from” approach that can be further derivatized for instance by the anchoring of chitosan (Fig. 13) or (ii) various (bio)macromolecules (Fig. 9, pathways B and C). These can either favor cell adhesion and improve blood compatibility by grafting heparin, concanavalin A or bovine serum albumin (BSA)[98-112] or avoid protein adhesion with poly(ethylene glycol) (PEG)[113-116], platelet activation thanks to selenocystamine[117] and even fungal colonization or bacterial fouling

when amphotericin B[118] or quaternary ammoniums salts[119] are immobilized onto the surface. Moreover, several research groups have developed original biosensors based on a polyDp coating post-functionalized with enzymes[120] such as glucose oxidase[121, 122] or antibodies[123-125].




Fig. 13. ATRP immobilized initiator on polyDp coating and controlled radical polymerization of 2-hydroxyethyl methacrylate (HEMA) followed by the immobilization of chitosan.[97]

Other functional groups can also be incorporated onto biomimetic coatings from functionalized catecholamine. Messersmith *et al.* have reported on the self-polymerization of norepinephrine(4, Fig. 2) in the same conditions. This molecule contains an additional hydroxyl group compared to dopamine.[126] Hence, as depicted in Fig. 14, after oxidative polymerization in the presence of a gold substrate, these secondary OH groups of the resulting poly(norepinephrine) can be then exploited to initiate the ring-opening

polymerization(ROP)[127] of lactones such as ϵ -caprolactone, thereby providing a biodegradable poly(ϵ -caprolactone) (PCL) coating on the surface.




Fig. 14. Ring-Opening Polymerization[127] of ϵ -caprolactone on poly(norepinephrine)-modified gold substrate.[126]

2.2. Polymerization of catechols catalyzed by enzymes.

Enzymatic polymerization is defined as “the *in vitro* polymerization of artificial substrate monomers catalyzed by an isolated enzyme *via* nonbiosynthetic (nonmetabolic) pathways”. [128, 129] Polyphenols can be produced by enzymatic polymerization of catechols under very mild conditions (in water at room temperature under atmospheric pressure and at neutral pH) without using any toxic reagents. Moreover, starting substrates are most often coming from renewable resources that make the enzymatic polymerization a great alternative to other synthetic pathways that required petrochemical sources. In this context, several enzymes can be involved in such polymerizations as discussed below.

Peroxidases such as soybean peroxidase (SBP) combined with hydrogen peroxide (H_2O_2) were, for example, used to polymerize catechol (**1**, Fig. 2). Indeed the peroxidase/ H_2O_2 combination is well-known to form an active enzyme substrate complex able to oxidize hydrogen donors such as phenols and amines. [15] Under these conditions, a polycatechol, incorporating both (2,3-dihydroxy-1,4-phenylene) (**13**) and (2-hydroxy-1,4-oxypyrenylene) (**14**) subunits (Fig. 15) was obtained. It is important to note that phenol groups of subunit **14**

are expected to have different chemical properties to catechols of **13** but this difference of reactivity is not discussed in the paper.

Dosoretz *et al.* performed enzymatic polymerization of catechols with horseradish peroxidase (HRP) in water and obtained polymers with high water solubility.[130] Nazari *et al.* compared poly(catechols) obtained by catalytic polymerization with HRP and a cationic metalloporphyrin as catalysts.[131] Tetrapyrroldiporphyrin seemed to be a more-efficient catalyst as final polymer has higher molecular weight and presented better thermal stability.




Fig. 15. (2,3-dihydroxy-1,4-phenylene) (**13**) and (2-hydroxy-1,4-oxyphenylene) (**14**) subunits found in the poly(catechol) structure.[15]

Flavonoids such as catechin (**8**, Fig. 2) were polymerized using HRP with a final average molecular weight ranging from 4000 to 12000 g/mol.[132] A polymerization mechanism proposal was based on radical polyrecombination processes to produce oligomers that can further recombine into polymers (Fig. 16), although no more details were given. However this pathway has been identified to compete with the probable formation of oxidation products and so the exact structure has not been perfectly identified yet. Poly(catechin) was also synthesized using HRP and the final product showed strong radical scavenging activity and inhibition effect against xanthine oxidase, a low-density lipoprotein responsible for the formation of uric acid.[133]




Fig. 16. Proposed structure for flavanolbased polymers.[132]

Additionally, caffeic acid (**5**, Fig. 2) was deposited onto gold surfaces functionalized with 4-aminothiophenol by dip-pen nanolithography.[134] It was then treated with HRP directly on the surface leading to formation of polymers incorporating quinoid subunits (**15**, Fig. 17).




Fig. 17. Structure (**15**) of poly(caffeic acid) synthesized by enzymatic polymerization using HRP.[134]

Another peroxidase, xanthine oxidase (XO), was used to polymerize several catecholamines in Tris-HCl buffer. Rose *et al.* observed that some of them, such as DOPA, were not polymerized presumably because of the negative influence on the enzyme activity of the α -carboxylic acid group contrary to dopamine.[135]

Poly(catechol)s, exclusively composed of (2-hydroxy-1,4-oxyphenylene) subunits (**14**, Fig. 15), were also successfully prepared by using oxidases such as laccase in combination with dissolved oxygen.[136] For example, catechin (**8**, Fig. 2), quercetin and rutin (**16** and **17**, respectively, Fig. 18) were oxidatively polymerized by laccase and, interestingly, both

polymer materials showed stronger superoxide scavenging activity compared to their monomer.[137-139]




Fig. 18.Chemical structures of quercetin (**16**) and rutin (**17**).

3. Side chain precursors

3.1. Polymerization of catechol based vinyl monomers.

Catechol side chain polymers can be conveniently prepared by radical polymerization of vinyl monomers incorporating a (un)protected catechol unit (Fig. 19).

3.1.1. *Starting from protected monomers.*

When vinyl monomers bearing protected catechols are considered, borax ($\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$) is mainly used as the protecting reagent by forming a cyclic bidentate-*o*-benzenediol subunitas depicted in Fig. 19.[140] The radical polymerization of the protected monomer occurs in water and leads to linear polymer chains. Catechol deprotection is carried out in acidic medium leading to polymers bearing pendant catechols. Other protecting groups can be employed such as 2,2-dimethoxypropane[141], benzyl bromide[142] or dichlorodiphenylmethane[143] to name only a few.




Fig. 19. Polymer architectures obtained from vinyl monomers bearing (un)protected catechol unit.

As an interesting example, protected dopamine acrylamide (**18**, Fig. 20) was homopolymerized using 2,2'-azobisisobutyronitrile (AIBN) as radical initiator in acetonitrile at 70°C for 3 days (Fig. 20). Deprotection of the catechols then occurred in a mixture of acetic acid, hydrobromic acid and trifluoroacetic acid at room temperature. The so-formed polymer bearing catechol groups on each monomer unit displayed strong adhesive properties towards wood when cured at high temperature (180°C) with amine-containing polymers such as poly(ethylenimine) (PEI). [144]




Fig. 20. Synthesis of poly(dopamine acrylamide) (19).[144]

Protected DOPA monomers have also been exploited for providing sustainable and durable AB coatings on stainless steel surfaces.[25] A linear homopolymer bearing DOPA repetitive units was synthesized by free radical polymerization of protected-DOPA methacrylamide (20, Fig. 21) in water using 4,4'-azobis(4-cyanopentanoic acid) (V-501) as initiator, followed by deprotection with HCl. The catechol groups of the polymer were then oxidized in water under basic conditions (pH = 10), leading to the corresponding water soluble polymer bearing quinone groups (21, Pox(mDOPA); Fig. 21). The sequential Layer-by-Layer[145]deposition of this polymer and poly(allylamine) (PAH) led to cross-linked films as the result of amine/quinone reactions between the two complementary partners (Fig. 22). Moreover, introducing an AB peptide (nisin) in the last layers of the multilayer film conferred strong AB properties to the material. Furthermore, due to the covalent anchoring of the peptide, the AB activity was maintained even after dipping the substrate in water for one night.




Fig. 21. Synthesis of Pox(mDOPA) (21).[25]




Fig. 22. Covalent LbL assembly for imparting robust AB property to stainless steel.[25]

Polymers bearing catechols can also be prepared starting from protected 3,4-dihydroxystyrene (22 and 23, Fig. 23)[146, 147] and were used as bio-inspired adhesives after deprotection.




Fig. 23. Chemical structures of 3,4-dimethoxystyrene (**22**)[146] and 3,4-di(OTBDMS)styrene (**23**)[147].

3.1.2. Starting from unprotected monomers.

When unprotected catechols were considered, a pioneering work described the copolymerization of DOPA methacrylamide (**24**, Fig. 24) with poly(ethylene glycol) diacrylate under UV irradiation in the presence of a photoinitiator (Fig. 25). This copolymerization led to hydrogels that are of prime interest as new adhesives for biomedical applications.[16]




Fig. 24. Monomers bearing catechol groups: DOPA methacrylamide (**24**)[16], dopamine methacrylamide (**25**)[148] and methyl ester DOPA methacrylamide (**26**)[149].




Fig. 25. Hydrogel preparation from the copolymerization of **24** with poly(ethylene glycol) diacrylate.[16]

Importantly, since catechols are well-known polymerization inhibitors by reacting with radicals with the formation of aryloxy free radicals,[150, 151] the radical polymerization of vinyl monomers bearing unprotected catechols is at first glance surprising. Nevertheless, several recent works of free-radically polymerized catechol monomers attest to the viability of this approach.[16, 148, 152-162] Dopamine methacrylamide (**25**, Fig. 24) was copolymerized with methoxyethyl acrylate to furnish a reversible adhesive on nanostructured surfaces.[148, 152] Copolymerization of **25** with a phosphate based monomer such as 2-(methacryloyloxy)ethyl phosphate allowed preparing underwater adhesives through complex coacervates when combined with a polymer bearing positive charges (protonated amine bearing polymers) and divalent cations (Ca^{2+} or Mg^{2+}) as depicted on Fig. 26.[153-155]




Fig. 26. Schematic representation of complex coacervates.[154]

Copolymers of **25** with 1*H*,1*H*-perfluorooctyl methacrylate were also synthesized in acetonitrile and coated onto various surfaces to impart them ultra-low surface free energy.[156] Substituting perfluorooctyl methacrylate by 2-aminoethyl methacrylamide provided copolymers useful for facile DNA immobilization onto various substrates (Fig. 27).[157] Oligomers of **25** and 2-(2-bromoisobutyryl) ethoxymethacrylate led to the design of macroinitiators for the preparation of poly(*N*-isopropylacrylamide) (PNIPAM) brushes on Ti plate by Si-ATRP.[158] Terpolymerization of **25** was also implemented, on the one hand, with methoxyethyl acrylate and ethylene glycol dimethacrylate for tuning the viscoelastic property of this pressure-sensitive adhesive[159, 160] and, on the other hand, with methoxyethyl acrylate and dodecyl quaternized 2-(dimethylamino)ethyl methacrylate for preparing antimicrobial surfaces.[161]




Fig. 27. Sequential method developed by Messersmith *et al.* to prepare DNA microarray on several substrates.[157]

Dual-action homopolymer of DOPA methacrylamide (**24**, Fig. 24) and copolymer of dopamine methacrylamide (**25**, Fig. 24) and *N*-[3-(dimethylamino)propyl] methacrylamide were synthesized by Alexander and coworkers.[162] Due to their positive charge and/or their catechol groups, these polymers were able to both force bacteria aggregation and suppress their quorum sensing (QS) signals. Successful bacterial capture has been confirmed with these two polymers. Furthermore, they were able to sequester bacteria without damaging cell viability, thereby rendering this new strategy very attractive for the conception of novel antimicrobial materials.

In all these works, neither the possible side reactions of propagating radicals with catechols nor their potential impact on the final polymer architecture are discussed. Polymers are always presented as linear structures. However, the radical polymerization of catechol bearing vinyl monomers is expected to provide (hyper)branched polymers or, even more, cross-linked materials, depending on the amount of catechols bearing monomers involved in the (co)polymerization process.[163] Indeed, according to the well-known reactivity of catechols with radicals, a catechol group of one polymer chain may react with a radical existing in

another chain during radical polymerization, thus forming an interchain C-O or C-C bond (Fig. 28). One or more bonds may exist between any two polymer chains leading to (hyper)branched polymers. Cross-linked materials should therefore be obtained when high amounts of catechol bearing monomers are used.




Fig. 28.Hyperbranching mechanism for the radical polymerization of vinyl monomers bearing unprotected catechols.

This expected branching reaction is however not discussed in none of the above mentioned manuscripts. Meanwhile, some authors recovered some insoluble materials when copolymerizing a conventional vinyl monomer with a catechol functionalized one, especially when large amounts of the latter were used.[148, 152, 156] Although not specifically mentioned in the above-discussed publications, these insoluble products are presumably the result of the cross-linking reactions promoted by the catechol based monomers.

The occurrence of this branching was demonstrated and illustrated by Detrembleur *et al.* by radically copolymerizing a DOPA derivative bearing a methacrylamide group (**26**, Fig. 24)[149, 163] with a methacrylate bearing an ammonium group ((2-(methacryloxy)ethyl) trimethylammonium chloride; DMAEMA⁺) in water at 50°C. The combination of Dynamic (DLS) and Static Light Scattering (SLS) experiments allowed to elucidate the hyperbranched architecture of the so-formed water soluble polyelectrolyte[163] of a high molar mass

($M_w > 10^6$ g/mol). Thanks to its free catechol groups, this copolymer P(mDOPA)-co-P(DMAEMA⁺) was used as a biomimetic glue for the strong anchoring of functional multilayers films onto stainless steel surfaces.[149, 163, 164] Antimicrobial and easy-cleaning stainless steel surfaces were obtained from multilayer films containing active biomolecules (nisin and mucin) based on that biomimetic glue.[165] The redox property of catechol was also exploited for the *in situ* formation of elemental silver nanoparticles (Ag⁰) by adding a silver nitrate (AgNO₃) aqueous solution to this DOPA-based hyperbranched copolymer.[149, 164] Indeed, catechols reduced Ag⁺ into Ag⁰ while the hyperbranched copolymer stabilized the so-formed nanoparticles. The LbL deposition of this silver loaded polycation with poly(styrene sulfonate) (PSS) as the negative counterpart led to highly biocidal coatings onto stainless steel.[149] Moreover, similar surface coatings were made from galvanized steel, thereby further indicating the high versatility of such bio-inspired glue for modifying various substrates. A protecting multilayer film against corrosion was built by alternating the deposition of P(mDOPA)-co-P(DMAEMA⁺) used as corrosion inhibitor with clays as negative counterparts that induced barrier properties. The whole process was conducted in water and did not release any toxic molecules in the environment while the esthetical aspect of the surface was preserved.[166]

3.2. Peptide synthesis of DOPA derivatives.

Because DOPA is largely present in the sequences of marine adhesive foot proteins, intensive research has been conducted on mimicking these structures by synthesizing peptides containing DOPA units. Some amino acids with protected side chains (lysine or glutamic acid for instances) were coupled with protected DOPA using the dicyclohexylcarbodiimide coupling method.[167, 168] Amongst these, peptides containing up to three DOPA amino acids were synthesized and coupled to a succinimidyl propionate-activated poly(ethylene glycol) (PEG-SPA) (Fig. 29) by reaction with their free NH₂ group at

the *N*-terminalextremity.[12]More particularly, Messersmith *et al.* studied the resistance of this conjugate to proteins adhesion when deposited on TiO₂ substrates and its ability to reduce marine algal fouling.[169]Finally, various kinds of surfaces (TiO₂ disks[170]and ureteral stents[171] for instances) coated with similar antiadhesive biomimetic peptides were found to strongly resist to both urinary film formation and bacterial attachment *in vitro*.





Fig. 29. Synthesis of poly(ethylene glycol) functionalized with DOPA units.[12]

Because DOPA amino acids are usually protected during peptide synthesis, final engineered macromolecules have a linear architecture with pendant DOPA moieties located at the extremity or within the peptide backbone (Fig. 3).Other peptides synthetic pathways and their final applications were reviewed elsewhere.[172]

3.2.1. Solid phase peptide synthesis.

Besides introducing this amino acid in marine adhesives mimic proteins,[173, 174] small DOPA peptides or co-peptides prepared by solid phase peptide synthesis were intensively exploited to strongly anchor antifouling macromolecules onto surfaces. For example,

Messersmith *et al.* have designed a catechol based peptidomimetic polymer (**27**, Fig. 30) for long-lasting fouling resistance of Ti surfaces.[175] These *N*-substituted glycine chains conferred to the substrates proteins and cells resistance for several months.



27

Fig. 30. Antifouling peptidomimetic polymer.[175]

DOPA has also been incorporated into a photopolymerizable fatty acid with the aim of elaborating adhesive stable spherical vesicles after self-assembly in chloroform.[176] Methoxy-PEG-NH₂ was coupled with a tetra-DOPA peptide to prepare metal core – polymer shell nanoparticles.[177]

3.2.2. Ring-opening polymerization of α -amino acid *N*-carboxyanhydrides (NCAs).

The synthesis of α -amino acid *N*-carboxyanhydrides (NCAs) by phosgenation of amino acids has been developed in the late 80's by Kricheldorf.[178] Deming *et al.* then prepared high molecular weight polypeptides bearing catechols by ring-opening polymerization of NCAs containing protected catechols followed by their deprotection (Fig. 31).[179] This method has the advantage to allow the preparation of large quantities of polymers and copolymers of tunable composition, opening the door to the development of new adhesives materials.[180-182]




Fig. 31. Synthesis of adhesive copolypeptides by ring-opening polymerization of α -amino acid *N*-carboxyanhydride (NCAs) monomers.

For example, multiple-interaction ligand has been developed by Hyeon *et al.* for the design of ultrastable and biocompatible nanoparticles.[183] Their strategy consists in the synthesis of a macromolecule bearing three main functional parts: a central one composed of charged PEI for electrostatic interactions with the negatively charged metal nanoparticles, a first external part consisting on poly(DOPA) able to strongly anchor the macromolecule on the nanoparticles, and a second external part composed of hydrophilic PEG segment required for solubilizing the nanoparticle/macromolecule assembly in water as a micelle (Fig. 32). This versatile strategy has been also extended to various nanoparticles such as Fe_3O_4 , MnO and Au that exhibited high stability in various harsh environments and might open the door to new relevant biomedical applications.





Fig. 32. Formation of water-dispersible nanoparticles through multiple-interaction ligand stabilization.[183]

Oligopeptides bearing DOPA units were also synthesized from amphiphilic block copolymers containing PEG blocks (hydrophilic part) and polyester blocks (hydrophobic part) in order to form adhesive hydrogels after photopolymerization of their methacrylate chain-ends (**28**, Fig. 33).[184] Biotinylated surfaces were also prepared *via* tri-DOPA peptide synthesis from a biotin-PEG bearing an amino group as chain end.[185] Indeed, catechol groups of DOPA were used to reduce gold or silver cations into metal nanoparticles with a stabilizing PEG-shell on their surfaces.



28

Fig. 33. Photocurable and biodegradable block copolymers.[184]

Interestingly, Kotov *et al.* prepared a terpolymer containing a tri-DOPA peptide, apoly(Lysine), and a PEG block (**29**, Fig. 34, A). The LbL deposition of aqueous solution of this copolymer and natural clays (Na^+ -Montmorillonite, MMT) afforded nacre-like films (Fig. 34, B).[186] These authors have nicely exploited the cross-linking ability of DOPA with Fe^{3+} [86, 187-190] to improve the mechanical properties of the nanohybrid films. Indeed, upon the addition of Fe^{3+} to Mefp1 (*Mytilus edulis* foot protein 1), the formation of a tris-catecholato-iron(III) complex was characterized (Fig. 35).[86] Then, iron reduction and oxidation of one DOPA bound can occur leading to the formation of a semiquinone radical which can further react with oxygen to generate other radical species that induce proteins radical-radical coupling and so the cross-linking (Fig. 35).[190] Formation of this tris-catecholato-iron(III) complex has recently been found to be strongly influenced by both iron/DOPA ratio[191] and pH[192].





Fig. 34. (A) Molecular structure of DOPA-Lys-PEG copolymer where $x \sim 53$ and $y \sim z \sim 3$; (B) LbL process between DOPA-Lys-PEG copolymer and MMT clay; digital photograph of a Fe^{3+} cross-linked 300 bilayer film of DOPA-Lys-PEG/clay (1); SEM cross-sectional view of Fe^{3+} cross-linked 300 bilayer film of DOPA-Lys-PEG/clay, arrows indicate the cross-section of the film (2).[186]




Fig. 35. Structure [86] and reactivity [190] of tris-catecholato-iron(III) complex.

3.3. Chemical ligation of catechol derivatives onto preformed (bio)polymers.

Another advantage of catechols relies on their faculty to be efficiently incorporated into polymer chains from preformed (bio)polymers. More particularly, a current trend in this domain is to use chemical ligation strategies between catecholamines (and derivatives) and appropriately selected activated polymers. The most useful ligation strategies are discussed below.

3.3.1. Grafting of catecholamines onto activated carboxylic acid functionalized polymers.




Fig. 36. Some strategies for the ligation of catecholamines onto polymers bearing carboxylic acid (activated by carbodiimide chemistry) (A), pentafluorophenyl (B), succinimidyl esters (C), and triazole activated esters (D).

The first developed strategy consists in reacting a polymer bearing side-chain carboxylic acid groups (Fig. 36, pathway A) with a catecholamine such as DOPA, dopamine or its derivatives in the presence of an activator like a water soluble carbodiimide compound (ethyl(dimethylaminopropyl) carbodiimide, EDC, for instance) to promote amidation. As an example, dopamine methacrylamide (**25**, Fig. 24) has been grafted onto poly(acrylic acid-co-butyl acrylate) in the presence of EDC to promote the coupling reaction between the carboxylic acid side groups of the copolymer and the amino group of the dopamine derivative. [193] This chemical modification has afforded adhesive property to this copolymer and an enhancement of its mechanical properties. Such coupling was also used to insert DOPA derivative (**7**, Fig.

2) into methacrylic triblock copolymers in order to improve the adhesion property of the so-formed hydrogels[194] or ii) to graft dopamine onto poly(acrylic acid) (PAA) to build robust multilayer films with PAH after oxidation by NaIO_4 [195]. In a similar way, Hammond *et al.* have grafted dopamine onto PAA with EDC in order to enhance LbL film stability with catechol-bearing PEI. This strategy allowed for the elaboration of multilayer materials displaying a better control of interlayer diffusion and so opened the door to new devices in drug delivery.[196]

Catecholamines can also be grafted to polymers bearing activated esters such as pentafluorophenyl or succinimide esters (Fig. 36; pathways B and C respectively). This grafting strategy has the advantage to occur at room temperature without any activator. For instance, dopamine was successfully grafted onto poly(pentafluorophenyl acrylate) and the conjugates were used for functionalizing nanoparticles such as TiO_2 , MoS_2 , MnO , or Fe_2O_3 [197-201] and dispersing TiO_2 , SnO_2 , ZnO or CdTe nanorods.[202-204]

Very recently, a well-defined difunctional poly(dopamine acrylamide-*co*-propargyl acrylamide) copolymer was also prepared from a reactive poly(pentafluorophenyl acrylate) homopolymer and exploited to sequentially modify a titanium surface (Fig. 37).[205] In a first step, the difunctional copolymer **30**, thanks to the presence of pendant catechol units into the polymer chain, was tethered onto a titanium substrate yielding a dense alkyne-functionalized Ti platform. Then, the copper-catalyzed azide-alkyne 1,3-dipolar cycloaddition (CuAAC) was employed to covalently graft fluorescent probes (Fluorescein, Rhodamine), PEG chains, and sugars (mannose, β -cyclodextrin).




Fig. 37. Bio-inspired surface functionalization by click chemistry.[205]

Additionally, other condensing agents can be found in the literature. For instance, poly(L-glutamic acid) was modified with dopamine by using 4-(4,6-dimethoxy-1,3,5-triazin-2-yl)-4-methylmorpholinium chloride (DMTMM) and further exploited in biodegradable capsules.[206]

3.3.2. Grafting of catecholamines onto hydroxyl functionalized polymers.

Hydroxyl-functional polymers can also be converted into *p*-nitrophenylcarbonate using *p*-nitrophenyl-chloroformate (NPC), and further modified by catecholamine (Fig. 38). For instance, nonfouling surfaces such as PTFE were prepared by covalent coupling of dopamine to hydroxyl-functional PEG.[207]




Fig. 38. Ligation of catecholamine onto hydroxyl-functionalized polymers using *p*-nitrophenyl-chloroformate (NPC) as an activator.

3.3.3. Grafting of catechol bearing a carboxylic acid group onto amino functionalized polymers.

Another approach consists in grafting a catechol derivative bearing a carboxylic acid group with amine functionalized biomolecules and biopolymers such as heparin[208, 209], hyaluronic acid[210-213], poly(L-lysine)[214] and soy protein[143] (Fig. 39). As an example, chitosan was functionalized with 3,4-dihydrocaffeic acid (**6**, Fig. 2) by coupling the primary amino groups of the polymer with the carboxylic acid of **6** using the carbodiimide activation.[215] This functionalized chitosan was then cross-linked with terminally thiolated Pluronic F-127 triblock copolymer to produce temperature-sensitive and adhesive sol-gel transition hydrogels. Modified chitosan with carboxylic acid functions was also immobilized on Ti surfaces pre-treated with polyDp in order to impart it antiadhesion property.[216]




Fig. 39. Strategy for the ligation of catechol derivatives bearing a carboxylic acid function using carbodiimide chemistry.

Synthetic polymers containing amino groups were also grafted according to similar strategies. For instance, PEI was modified by 3,4-dihydrocaffeic acid (**6**, Fig. 2) in the presence of EDC to form an universal surface primer for multilayer assembly[217] or to reinforce the mechanical properties of CTNs fibers.[218]

Another well-known strategy consists in forming activated esters with an uronium salt such as *O*-(benzotriazol-1-yl)-*N,N,N',N'*-tetramethyluroniumhexafluorophosphate (HBTU) (Fig. 36; pathway D). This coupling reaction occurs at room temperature in the presence of triethylamine and 1-hydroxybenzotriazole hydrate (HOBt). Compound **6** was so coupled using these coupling reagents onto a 4-arm PEG-NH₂. The resulting catechol end-functionalized PEG precursors were *in situ* transformed into amultiblock copolymers in the presence of linear diacid-functionalized PCL. When coated onto a biologic mesh used for hernia repair, this adhesive polymer demonstrated adhesive strengths significantly higher than fibrin.[219] In addition, more recently, this intriguing adhesive material was used to greatly improve the repair of injured Achilles tendons.[220]

3.3.4. Electrochemical grafting of catechol units onto amino functionalized polymers.

Chitosan films electrodeposited onto gold surfaces were modified by electrochemical oxidation of catechols (Fig. 40).[221, 222] Gold crystals were first immersed in a chitosan solution (0.1%, pH 5.3) and potential was swept in the reducing direction. The substrates were then transferred into several aqueous catechol solutions under oxidative conditions promoting its covalent grafting onto the films. These modified surfaces behave as electrons donor and electrons acceptor in the presence of biological oxidants (O₂) and reducers (NADPH), respectively. Such phenolic matrices may play important roles in understanding biological

phenomena such as electron transfer, mode-of-action of bactericidal antibiotics, neuromelanins activity, etc.




Fig. 40. Synthetic pathway for electro-modification of chitosan with catechols.[221]

3.4. Enzymatic derivatization of (bio)polymers bearing tyrosine moieties

Biopolymer-polyphenol conjugates with water resistant adhesive property can also be produced using enzymes such as tyrosinase. Tyrosinase can oxidize the tyrosine amino acids of proteins into catechols (Fig. 41, pathway A) but also into quinones (Fig. 41, pathway B) depending on the reaction conditions. In the presence of a reducer such as ascorbic acid, tyrosine groups are converted into the adhesive DOPA amino acids by tyrosinase in aerated conditions.[223]




Fig. 41. (A) Conversion of tyrosine amino acids into DOPA by tyrosinase in the presence of a reducer, (B) Oxidation of phenol or catechol derivatives into reactive *o*-quinones using tyrosinase, followed by the grafting of amino-functionalized biomolecules/biopolymers

Yamamoto *et al.* exploited this strategy in various publications[224, 225] and, for example, synthesized chitosan derivatives incorporating a tetrapeptide based tyrosine residue. These phenolic amino acids were then converted into DOPA by tyrosinase, thus affording, after the cross-linking with the grafted peptide chains, a reinforced polysaccharide hybrid fiber.[226]

Tyrosinase was also used to couple different phenolic antioxidants (caffeic acid and chlorogenic acid) to wool fiber proteins[227] by oxidizing them into highly reactive *o*-quinones that rapidly reacted with the proteins *via* their amino groups (Fig. 41, (B)). Other biopolymers (poly(ϵ -lysine) and gelatin) and synthetic polymers (poly(allylamine) and polyhedral oligomeric silsesquioxane) have been modified with phenolic compounds following the same strategy. Such type of functionalization has been reviewed elsewhere.[228]

4. End chain precursors

4.1. Grafting of catechol unit(s) onto chain-ends by chemical ligation.

PEG polymers have also been functionalized at chain-ends with molecules bearing catechols following strategies as those depicted in Fig. 36. As far as EDC coupling agent is

concerned[229-233], final products were usually designed for metal nanoparticles stabilization such as FePt or Fe₃O₄ in the biomedical field (Fig. 36, pathway A). For example, EDC was used to catalyze the formation of amide bonds between Au-Fe₃O₄-Dopamine-PEG-COOH nanoparticles and the epidermal growth factor receptor antibody. These magnetic and optical active dumbbell Au-Fe₃O₄ nanoparticles were then exploited to image binding events between the modified nanoparticles and A431 cells.[233]

Catechol derivatives were also coupled to one *N*-hydroxysuccinimidyl activated chain-end polymer mostly to elaborate stable biomimetic surfaces with protein, bacterial-resistant adlayers or antimicrobial properties (Fig. 36, pathway C).[234-238] More recently, nitrocatecholamines were used to end-functionalize a four-arm star PEG-(NHS)₄. Interestingly, these nitrocatechol functionalized polymers were employed to generate various covalently and metal-cross-linked responsive gels and coatings that can be on demand photodegraded upon light exposure (Fig. 42).[239]




Fig. 42. Strategies to prepare photoreactive films based on nitrodopamine derivatives: through metallic complexation (A) or covalent bonds (B).

PEG modification with a catechol function using HBTU/HOBt as coupling reagents has been widely studied in the literature and is of prime interest for biological applications where a robust polymer anchoring is needed. Functionality has been integrated at one chain-end[17, 240] or at several chain-ends when multiple arms PEG-based polymers were concerned[241-244]. For instance, Messersmith *et al.* worked on the gelation conditions (nature and concentration of oxidizing agent, (un)protected *N*-terminal side chain ...) of several DOPA modified PEG and obtained different hydrogels from star-shaped architectures such as those

depicted in Fig. 43, **31**.^[245] Recently, these mussel glue hydrogels (R=H) were also employed *in vivo* as promising elastomeric tissue sealant for repairing fetal membranes^[145] and for islet cell encapsulation.^[244]




Fig. 43. Examples of multiple arm-PEG modified with DOPA moieties.

Starting from the same architecture (R = NHBoc), they developed self-healing hydrogels based on catechol-Fe³⁺ complexes and controlled their mechanical properties via pH change and the nature of the interpolymer cross-linking.^[192] The tris-catechol-Fe³⁺ cross-linked gels exhibited better viscoelastic properties than the mono-catechol-Fe³⁺ complex.

Peptide dendritic ligands containing lysine or glutamic acid were also prepared using the same coupling agents from protected dopamine and added then to magnetic nanoparticles following the ligand-exchange method.^[246] These modified nanoparticles potentially represent straightforward platforms for the attachment of biological active molecules of interest for biomedical applications.

Additionally, by exploiting reversible boronic ester linkages, Messersmith *et al.* succeeded in the creation of intriguing pH-responsive, self-healing hydrogels from catechol-modified

multiple arms-PEG (Fig. 44).[247]Indeed, by mixing catechol end-chain functionalized 4-arm PEG and 1,3-benzenediboronic acid, boronate cross-linked hydrogels were conveniently obtained under basic conditions (pH above the diolpK_a, 9 in this case) within 30 minutes at 20°C. Interestingly, these boronate ester bonds were completely dissociated at pH below 3, leading back to starting materials. Self-healing property has also been demonstrated between two pieces of fractured gels that healed autonomously and rapidly without the use of cross-linking agents thanks to the presence of free boronic acid and catechol units at these frontiers.




Fig. 44. Schematic representation of self-healing and pH-responsive hydrogels developed by Messersmith *et al.*.[247]

Trichloro-*s*-triazine (TsT) was used as linker between monomethoxy-poly(ethylene glycol) (mPEG) and dopamine to stabilize Fe₃O₄ nanoparticles.[248]Enzymatically degradable adhesive hydrogels were synthesized by coupling an Alanine-Alanine dipeptide-modified branched PEG and **6** with benzotriazol-1-yl-oxy-tripyrrolidinophosphonium hexafluorophosphate (PyBOP), followed by oxidative coupling of the catechol chain-ends by the addition of NaIO₄ (Fig. 45).[249]




Fig. 45. Enzymatically degradable adhesive hydrogels.[249]

Dopamine was also linked to oligonucleotides bearing a carboxylic acid end group by using *N*-hydroxysuccinimide ester as the activator.[250] This activator was also involved in the modification of poly(ethylene oxide)-poly(propylene oxide)-poly(ethylene oxide) (PEO-PPO-PEO) triblock copolymers with DOPA to improve its bioadhesion.[251]

4.2. Elaboration of catechol end-functionalized polymers via controlled/living and electrochemical polymerizations techniques.

During the last decade, controlled radical polymerization (CRP) techniques such as Atom Transfer Radical Polymerization (ATRP)[252-254] and Reversible Addition-Fragmentation chain Transfer polymerization (RAFT),[255-257] to name a few, have been proven to be very versatile techniques to introduce end-groups on a well-defined polymer chain. Obviously, much effort has been devoted over the last few years to prepare well-defined catechol end-functionalized synthetic polymers using CRP techniques with the ultimate goal of creating (patterned) polymer brushes or stabilizing nanoparticles via a “grafting to” approach. In this context, ATRP and RAFT were found to be highly efficient procedures for the preparation of the sus-mentioned polymers by using catechol based initiators (32-35, Fig. 46) or chain transfer agents (36 and 37, Fig. 46), respectively.




Fig. 46. Catechol derivatives as polymerization initiators in solution; ATRP initiators **32**[258], **33**[259], **34**[260] and **35**[261], RAFT agents **36**[262] and **37**[20].

When ATRP is concerned, zwitterionic polymers were prepared in solution from protected catecholic initiators (**32**, **33** and **34**, Fig. 46) and ultra low fouling property was imparted to various surfaces after their immobilization.[258-260, 263] Copolymers of di(ethylene glycol) methyl ether methacrylate (MEO₂MA) and poly((ethylene glycol) methyl ether methacrylate) (MAPEG) were synthesized from **35** (Fig. 46) and were then used for the stabilization of Fe₃O₄ nanoparticles.[261] Such modified nanoparticles were further studied for their ability to interchange their hydrophilic/hydrophobic character.[264] Indeed, they were hydrophobic enough to adsorb at the air/water interface but can simultaneously be squeezed out from the interface if the packing density exceeds a critical value. Such behavior is very promising for biomedical applications such as crossing biological membranes. The thermo-responsive character of these copolymers was also nicely exploited for inducing the controlled

nanoparticles agglomeration that enhanced the contrast ability of Fe₃O₄ in magnetic resonance imaging applications.[229]

Catechols bearing a RAFT agent (**36**, Fig. 46) were also implemented for the preparation of well-defined poly(*tert*-butyl acrylate), poly(*N*-isopropylacrylamide) (PNIPAM) and poly(styrene) that were then immobilized onto Ti surfaces.[262] In this study, the immobilization of polymers on the titanium surface was monitored by using surface plasmon resonance technology that allowed estimating the surface coverage (Γ) of the grafted polymers onto the sensor surface. The dopamine chemistry was also successfully exploited for the preparation of thermoresponsive nanodiamond-functionalized PNIPAM particles from well-defined dopamine end-functionalized PNIPAM. These particles exhibited a reversible Lower Critical Soluble Transition (LCST) phase transition at around 32°C leading to the formation of small aggregates with a particle size of ~90 nm. Because of its simple, gentle nature and versatility, this strategy is an avenue for the preparation of other responsive (pH, redox, etc...) functional nanodiamond particles for nanobiotechnology applications.[265]

Fig. 47 points out that a large range of grafted polymer brushes can also be prepared, from the different catechol based anchors (**37-42**), by:

- i) performing CuAAC reactions[266, 267] between either catechol-alkyne[268] or catechol-azide[269] tethered surfaces and appropriate complementary functionalized end-terminated polymers. For instance, the alkyne-modified dopamine anchor **40** was immobilized onto Fe₃O₄ nanoparticles giving rise to “clickable” nanoparticles.[268] Then, an azido-end-decorated PEG was clicked onto these nanoparticles to render these magnetic nanoparticles soluble in water. Opposite strategy was also applied to titanium surfaces where an azide-functionalized dopamine **41** was anchored to the surface prior to coupling to an alkyne-functional electroactive or fluorinated probe.[269]

- ii) using “grafting from” procedures from catechol functionalized surfaces able to undergo a CRP (*e.g.* ATRP[18, 270-276] and RAFT[20]) or ROMP[19] (Ring-Opening Metathesis Polymerization[277]) polymerizations respectively. Of these polymerization techniques, the ATRP has been without doubt the most commonly used. This has notably been applied to build both antifouling and cell adhesive surfaces by grafting, for instance, PEG and zwitterionic polymers, respectively.[18, 270, 274] Poly(styrene) brushes were also grown from a catechol based RAFT transfer agent (**37**, Fig. 46) immobilized on Ti[87]₄-modified ITO.[20] Interestingly, these brushes were removed from the surface by dipping the surface in a phosphate buffer (pH 9.0), the Ti-diol complex being easily dissociated under weak basic conditions. ROMP was also exploited to grow polymer brushes from various surfaces modified with **39** (Fig. 47).[19] This approach allowed the elaboration of low surface energy by grafting perfluoroalkyl-substituted polymer brushes and also to immobilize polymers onto patterned surfaces by using microcontact printing (μ CP).
- iii) performing electropolymerization from TiO₂ nanotubes whose inner walls are coated by a catechol bearing a pyrrole group (**42**, Fig. 47).[278] These modified nanotubes presented a smaller charge transfer resistance and are potential candidates for fabricating ordered organic/inorganic p-n heterojunctions.




Fig. 47. Strategies to prepare polymer brushes onto surfaces: ROMP[19], RAFT[20], ATRP[18], CuAAC reaction[268, 269] and electropolymerization[278].

5. Conclusions.

The main aim of this review was to present the most important and straightforward synthetic methods allowing the incorporation of catechol units into polymer chains and to highlight the importance of these catechols for further functionalization of the macromolecules. Indeed, the field of catechol-containing polymers, owing to their fascinating intrinsic chemical properties and their practical applications, has greatly expanded over the past decade. More particularly, the combination of synthetic versatility, rich functionality and inherent binding properties towards various organic and inorganic surfaces make this class of polymers useful for many applications including synthetic adhesives and coatings, sensors, bioactive and self-healing materials, smart hydrogels and photovoltaic materials.

While most of the earlier efforts were primarily focused on the incorporation of catechol units into the main chains of polymers, by exploiting its redox properties, new methods have been explored more recently, providing for facile synthetic access to functional catechol-containing materials with advanced properties. Many biomimetic adhesive peptides incorporating side-chain catechol fragments, were, for example, readily prepared by solid-state peptide synthesis or by ring-opening polymerization of α -amino acid *N*-carboxyanhydrides. Recently, ligation techniques have also been employed i) to conveniently elaborate catechol end- and side-functionalized polymer materials, displaying self-healing and stimuli-responsive properties, from preformed activated (bio)polymers and ii) to construct, *via* « click » chemistry, bio-inspired functionalized surfaces. More recently, Living/Controlled Polymerization techniques, such as ATRP, RAFT and ROMP, have also emerged as powerful and versatile techniques allowing the immobilization, using both « grafting from » and « grafting onto » strategies, of well-defined end-decorated catechol polymers onto different substrates. Surfaces and nanoparticles with controllable interface properties and very promising biomedical applications have been created using such approaches.

Throughout this review, we have shown that the various reactivity of catechols in combination with the different polymerization methods available allow a plethora of catechol containing polymers with variable structures and interesting properties to be produced. However, we firmly believe that the development of catechol-based polymers is still a burgeoning field and that exciting new catechol-based materials with applications in interesting new fields will be reported.

Acknowledgements

The research was partly supported by BELSPO (IUAP VI/27) and the Walloon Region (PPP program BIOCOAT). We thank all the BIOCOAT team for its contribution. C. Detrembleur is Senior Research Associate by the F.R.S.-FNRS and thanks F.R.S.-FNRS for financial support.

References

- [1] Krumenacker L, Constantini M, Pontal P, Sentenac J. Hydroquinone, resorcinol, and catechol. Kirk-Othmer, Encyclopedia of Chemical Technology. New York: John Wiley & Sons; 1995. p. 996-1014.
- [2] Waite JH, Tanzer ML. Polyphenolic substances of *Mytilus edulis*: novel adhesive containing L-dopa and hydroxyproline. *Science* 1981;212:1038-40.
- [3] Deming TJ. Mussel byssus and biomolecular materials. *Curr Opin Chem Biol* 1999;3:100-5.
- [4] Yu M, Hwang J, Deming TJ. Role of L-3,4-Dihydroxyphenylalanine in Mussel Adhesive Proteins. *J Am Chem Soc* 1999;121:5825-6.
- [5] Waite JH. Adhesion a la moule. *Integr Comp Biol* 2002;42:1172-80.
- [6] Brubaker CE, Messersmith PB. The Present and Future of Biologically Inspired Adhesive Interfaces and Materials. *Langmuir* 2012;28:2200-5.

- [7] Zhao H, Waite JH. Linking Adhesive and Structural Proteins in the Attachment Plaque of *Mytilus californianus*. *J Biol Chem* 2006;281:26150-8.
- [8] Lee H, Scherer NF, Messersmith PB. Single-molecule mechanics of mussel adhesion. *Proc Natl Acad Sci USA* 2006;103:12999-3003.
- [9] Lin Q, Gourdon D, Sun C, Holten-Andersen N, Anderson TH, Waite JH, Israelachvili JN. Adhesion mechanisms of the mussel foot proteins mfp-1 and mfp-3. *Proc Natl Acad Sci USA* 2007;104:3782-6.
- [10] Ye Q, Zhou F, Liu W. Bioinspired catecholic chemistry for surface modification. *Chem Soc Rev* 2011;40:4244-58.
- [11] Anderson TH, Yu J, Estrada A, Hammer MU, Waite JH, Israelachvili JN. The Contribution of DOPA to Substrate-Peptide Adhesion and Internal Cohesion of Mussel-Inspired Synthetic Peptide Films. *Adv Funct Mater* 2010;20:4196-205.
- [12] Dalsin JL, Lin L, Tosatti S, Voeroes J, Textor M, Messersmith PB. Protein Resistance of Titanium Oxide Surfaces Modified by Biologically Inspired mPEG-DOPA. *Langmuir* 2005;21:640-6.
- [13] Lee BP, Messersmith PB, Israelachvili JN, Waite JH. Mussel-inspired adhesives and coatings. *Annu Rev Mater Res* 2011;41:99-132.
- [14] Lee H, Dellatore SM, Miller WM, Messersmith PB. Mussel-Inspired Surface Chemistry for Multifunctional Coatings. *Science* 2007;318:426-30.
- [15] Dubey S, Singh D, Misra RA. Enzymatic synthesis and various properties of poly(catechol). *Enzyme Microb Technol* 1998;23:432-7.
- [16] Lee BP, Huang K, Nunalee FN, Shull KR, Messersmith PB. Synthesis of 3,4-dihydroxyphenylalanine (DOPA) containing monomers and their co-polymerization with PEG-diacrylate to form hydrogels. *J Biomater Sci Polym Ed* 2004;15:449-64.
- [17] Dalsin JL, Hu B-H, Lee BP, Messersmith PB. Mussel Adhesive Protein Mimetic Polymers for the Preparation of Nonfouling Surfaces. *J Am Chem Soc* 2003;125:4253-8.
- [18] Fan X, Lin L, Dalsin JL, Messersmith PB. Biomimetic Anchor for Surface-Initiated Polymerization from Metal Substrates. *J Am Chem Soc* 2005;127:15843-7.

- [19] Ye Q, Wang X, Li S, Zhou F. Surface-Initiated Ring-Opening Metathesis Polymerization of Pentadecafluorooctyl-5-norbornene-2-carboxylate from Variable Substrates Modified with Sticky Biomimic Initiator. *Macromolecules* 2010;43:5554-60.
- [20] Liu J, Yang W, Zareie HM, Gooding JJ, Davis TP. pH-Detachable Polymer Brushes Formed Using Titanium-Diol Coordination Chemistry and Living Radical Polymerization (RAFT). *Macromolecules* 2009;42:2931-9.
- [21] Kahn V, Zakin V. Effect of salicylhydroxamic acid (SHAM) on DL-DOPA oxidation by mushroom tyrosinase and by NaIO₄. *J Food Biochem* 2000;24:399-415.
- [22] Herlinger E, Jameson RF, Linert W. Spontaneous autoxidation of dopamine. *J Chem Soc Perkin Trans 2* 1995:259-63.
- [23] Jiang J, Zhu L, Zhu L, Zhu B, Xu Y. Surface Characteristics of a Self-Polymerized Dopamine Coating Deposited on Hydrophobic Polymer Films. *Langmuir* 2011;27:14180-7.
- [24] Burzio LA, Waite JH. Cross-Linking in Adhesive Quinoproteins: Studies with Model Decapeptides. *Biochemistry* 2000;39:11147-53.
- [25] Faure E, Lecomte P, Lenoir S, Vreuls C, Van De Weerd C, Archambeau C, Martial J, Jerome C, Duwez A-S, Detrembleur C. Sustainable and bio-inspired chemistry for robust antibacterial activity of stainless steel. *J Mater Chem* 2011;21:7901-4.
- [26] Li B, Liu W, Jiang Z, Dong X, Wang B, Zhong Y. Ultrathin and Stable Active Layer of Dense Composite Membrane Enabled by Poly(dopamine). *Langmuir* 2009;25:7368-74.
- [27] Pan F, Jia H, Qiao S, Jiang Z, Wang J, Wang B, Zhong Y. Bioinspired fabrication of high performance composite membranes with ultrathin defect-free skin layer. *J Membr Sci* 2009;341:279-85.
- [28] Chen J, Chen X, Yin X, Ma J, Jiang Z. Bioinspired fabrication of composite pervaporation membranes with high permeation flux and structural stability. *J Membr Sci* 2009;344:136-43.
- [29] Ryou M-H, Lee YM, Park J-K, Choi JW. Mussel-Inspired Polydopamine-Treated Polyethylene Separators for High-Power Li-Ion Batteries. *Adv Mater* 2011;23:3066-70.

- [30] Liu A, Zhao L, Bai H, Zhao H, Xing X, Shi G. Polypyrrole Actuator with a Bioadhesive Surface for Accumulating Bacteria from Physiological Media. *ACS Appl Mater Interfaces* 2009;1:951-5.
- [31] Wang J, Xiao L, Zhao Y, Wu H, Jiang Z, Hou W. A facile surface modification of Nafion membrane by the formation of self-polymerized dopamine nano-layer to enhance the methanol barrier property. *J Power Sources* 2009;192:336-43.
- [32] Xi Z-Y, Xu Y-Y, Zhu L-P, Wang Y, Zhu B-K. A facile method of surface modification for hydrophobic polymer membranes based on the adhesive behavior of poly(DOPA) and poly(dopamine). *J Membr Sci* 2009;327:244-53.
- [33] Zhang H, Hu H, Ye W, Zhou F. Conferring polytetrafluoroethylene micropowders with hydrophilicity using dopamine chemistry and the application as water-based lubricant additive. *J Appl Polym Sci* 2011;122:3145-51.
- [34] Ou J, Wang J, Liu S, Zhou J, Ren S, Yang S. Microtribological and electrochemical corrosion behaviors of polydopamine coating on APTS-SAM modified Si substrate. *Appl Surf Sci* 2009;256:894-9.
- [35] Kang SM, You I, Cho WK, Shon HK, Lee TG, Choi IS, Karp JM, Lee H. One-Step Modification of Superhydrophobic Surfaces by a Mussel-Inspired Polymer Coating. *Angew Chem Int Ed* 2010;49:9401-4.
- [36] Ou J, Wang J, Zhou J, Liu S, Yu Y, Pang X, Yang S. Construction and study on corrosion protective property of polydopamine-based 3-layer organic coatings on aluminum substrate. *Prog Org Coat* 2010;68:244-7.
- [37] Ou J-F, Wang J-Q, Qiu Y-N, Liu L-Z, Yang S-R. Mechanical property and corrosion resistance of zirconia/polydopamine nanocomposite multilayer films fabricated via a novel non-electrostatic layer-by-layer assembly technique. *Surf Interface Anal* 2011;43:803-8.
- [38] Yang SH, Kang SM, Lee K-B, Chung TD, Lee H, Choi IS. Mussel-Inspired Encapsulation and Functionalization of Individual Yeast Cells. *J Am Chem Soc* 2011;133:2795-7.

- [39] Kim BH, Lee DH, Kim JY, Shin DO, Jeong HY, Hong S, Yun JM, Koo CM, Lee H, Kim SO. Mussel-Inspired Block Copolymer Lithography for Low Surface Energy Materials of Teflon, Graphene, and Gold. *Adv Mater* 2011;23:5618-22.
- [40] Yang L-P, Phua S-L, Teo J-KH, Toh C-L, Lau S-K, Ma J, Lu X-H. A Biomimetic Approach to Enhancing Interfacial Interactions: Polydopamine-Coated Clay as Reinforcement for Epoxy Resin. *ACS Appl Mater Interfaces* 2011;3:3026-32.
- [41] Gao J, Liang G, Cheung JS, Pan Y, Kuang Y, Zhao F, Zhang B, Zhang X, Wu EX, Xu B. Multifunctional Yolk-Shell Nanoparticles: A Potential MRI Contrast and Anticancer Agent. *J Am Chem Soc* 2008;130:11828-33.
- [42] Zhou W-H, Lu C-H, Guo X-C, Chen F-R, Yang H-H, Wang X-R. Mussel-inspired molecularly imprinted polymer coating superparamagnetic nanoparticles for protein recognition. *J Mater Chem* 2010;20:880-3.
- [43] Yu B, Liu J, Liu S, Zhou F. Pdop layer exhibiting zwitterionicity: a simple electrochemical interface for governing ion permeability. *Chem Commun* 2010;46:5900-2.
- [44] Bernsmann F, Ponche A, Ringwald C, Hemmerle J, Raya J, Bechinger B, Voegel J-C, Schaaf P, Ball V. Characterization of Dopamine-Melanin Growth on Silicon Oxide. *J Phys Chem C* 2009;113:8234-42.
- [45] Martma K, Habicht K-L, Ramirez XM, Tepp K, Kaeaembre T, Volobujeva O, Shimmo R. Polydopamine as an adhesive coating for open tubular capillary electrochromatography. *Electrophoresis* 2011;32:1054-60.
- [46] Wu C, Fan W, Chang J, Xiao Y. Mussel-inspired porous SiO₂ scaffolds with improved mineralization and cytocompatibility for drug delivery and bone tissue engineering. *J Mater Chem* 2011;21:18300-7.
- [47] Kang S, Elimelech M. Bioinspired Single Bacterial Cell Force Spectroscopy. *Langmuir* 2009;25:9656-9.
- [48] Ouyang R, Lei J, Ju H. Surface molecularly imprinted nanowire for protein specific recognition. *Chem Commun* 2008:5761-3.

- [49] Zhang Y, Wang H, Nie J, Zhou H, Shen G, Yu R. Mussel-inspired fabrication of encoded polymer films for electrochemical identification. *Electrochem Commun* 2009;11:1936-9.
- [50] Bernsmann F, Frisch B, Ringwald C, Ball V. Protein adsorption on dopamine-melanin films: Role of electrostatic interactions inferred from ζ -potential measurements versus chemisorption. *J Colloid Interface Sci* 2010;344:54-60.
- [51] Ye W, Wang D, Zhang H, Zhou F, Liu W. Electrochemical growth of flowerlike gold nanoparticles on polydopamine modified ITO glass for SERS application. *Electrochim Acta* 2010;55:2004-9.
- [52] Yang F, Zhao B. Adhesion properties of self-polymerized dopamine thin film. *Open Surface Science Journal* 2011;3:115-22.
- [53] Pezzella A, Panzella L, Natangelo A, Arzillo M, Napolitano A, d'Ischia M. 5,6-Dihydroxyindole Tetramers with Anomalous Interunit Bonding Patterns by Oxidative Coupling of 5,5',6,6'-Tetrahydroxy-2,7'-biindolyl: Emerging Complexities on the Way toward an Improved Model of Eumelanin Buildup. *J Org Chem* 2007;72:9225-30.
- [54] Xu LQ, Yang WJ, Neoh K-G, Kang E-T, Fu GD. Dopamine-Induced Reduction and Functionalization of Graphene Oxide Nanosheets. *Macromolecules* 2010;43:8336-9.
- [55] Ku SH, Ryu J, Hong SK, Lee H, Park CB. General functionalization route for cell adhesion on non-wetting surfaces. *Biomaterials* 2010;31:2535-41.
- [56] Ku SH, Lee JS, Park CB. Spatial Control of Cell Adhesion and Patterning through Mussel-Inspired Surface Modification by Polydopamine. *Langmuir* 2010;26:15104-8.
- [57] Sun K, Song L, Xie Y, Liu D, Wang D, Wang Z, Ma W, Zhu J, Jiang X. Using Self-Polymerized Dopamine to Modify the Antifouling Property of Oligo(ethylene glycol) Self-Assembled Monolayers and Its Application in Cell Patterning. *Langmuir* 2011;27:5709-12.
- [58] Sun K, Xie Y, Ye D, Zhao Y, Cui Y, Long F, Zhang W, Jiang X. Mussel-Inspired Anchoring for Patterning Cells Using Polydopamine. *Langmuir* 2012;28:2131-6
- [59] Postma A, Yan Y, Wang Y, Zelikin AN, Tjipto E, Caruso F. Self-Polymerization of Dopamine as a Versatile and Robust Technique to Prepare Polymer Capsules. *Chem Mater* 2009;21:3042-4.

- [60] Yu B, Wang DA, Ye Q, Zhou F, Liu W. Robust polydopamine nano/microcapsules and their loading and release behavior. *Chem Commun* 2009;6789-91.
- [61] Liu R, Mahurin SM, Li C, Unocic RR, Idrobo JC, Gao H, Pennycook SJ, Dai S. Dopamine as a Carbon Source: The Controlled Synthesis of Hollow Carbon Spheres and Yolk-Structured Carbon Nanocomposites. *Angew Chem Int Ed* 2011;50:6799-802.
- [62] Zhang L, Shi J, Jiang Z, Jiang Y, Meng R, Zhu Y, Liang Y, Zheng Y. Facile Preparation of Robust Microcapsules by Manipulating Metal-Coordination Interaction between Biomineral Layer and Bioadhesive Layer. *ACS Appl Mater Interfaces* 2011;3:597-605.
- [63] Liu Q, Yu B, Ye W, Zhou F. Highly Selective Uptake and Release of Charged Molecules by pH-Responsive Polydopamine Microcapsules. *Macromol Biosci* 2011;11:1227-34.
- [64] Zhang L, Shi J, Jiang Z, Jiang Y, Qiao S, Li J, Wang R, Meng R, Zhu Y, Zheng Y. Bioinspired preparation of polydopamine microcapsule for multienzyme system construction. *Green Chem* 2011;13:300-6.
- [65] Xu H, Liu X, Wang D. Interfacial Basicity-Guided Formation of Polydopamine Hollow Capsules in Pristine O/W Emulsions - Toward Understanding of Emulsion Template Roles. *Chem Mater* 2011;23:5105-10.
- [66] Cui J, Wang Y, Postma A, Hao J, Hosta-Rigau L, Caruso F. Monodisperse Polymer Capsules: tailoring Size, Shell Thickness, and Hydrophobic Cargo Loading via Emulsion Templating. *Adv Funct Mater* 2010;20:1625-31.
- [67] LaVoie MJ, Ostaszewski BL, Weihofen A, Schlossmacher MG, Selkoe DJ. Dopamine covalently modifies and functionally inactivates parkin. *Nat Med* 2005;11:1214-21.
- [68] Merritt ME, Christensen AM, Kramer KJ, Hopkins TL, Schaefer J. Detection of Intercatechol Cross-Links in Insect Cuticle by Solid-State Carbon-13 and Nitrogen-15 NMR. *J Am Chem Soc* 1996;118:11278-82.
- [69] Xu R, Huang X, Hopkins TL, Kramer KJ. Catecholamine and histidyl protein cross-linked structures in sclerotized insect cuticle. *Insect Biochem Mol Biol* 1997;27:101-8.

- [70] Lee H, Rho J, Messersmith PB. Facile conjugation of biomolecules onto surfaces via mussel adhesive protein inspired coatings. *Adv Mater* 2009;21:431-4.
- [71] Waite JH. Mussel power. *Nat Mater* 2008;7:8-9.
- [72] Lyngø ME, van der Westen R, Postma A, Stedler B. Polydopamine-a nature-inspired polymer coating for biomedical science. *Nanoscale* 2011;3:4916-28.
- [73] Kang SM, Park S, Kim D, Park SY, Ruoff RS, Lee H. Simultaneous Reduction and Surface Functionalization of Graphene Oxide by Mussel-Inspired Chemistry. *Adv Funct Mater* 2011;21:108-12.
- [74] Kaminska I, Das MR, Coffinier Y, Niedziolka-Jonsson J, Sobczak J, Woisel P, Lyskawa J, Opalło M, Boukherroub R, Szunerits S. Reduction and Functionalization of Graphene Oxide Sheets Using Biomimetic Dopamine Derivatives in One Step. *ACS Appl Mater Interfaces* 2012;4:1016-20.
- [75] Lee Y, Park TG. Facile Fabrication of Branched Gold Nanoparticles by Reductive Hydroxyphenol Derivatives. *Langmuir* 2011;27:2965-71.
- [76] Qu W-G, Wang S-M, Hu Z-J, Cheang T-Y, Xing Z-H, Zhang X-J, Xu A-W. In Situ Synthesis of Gold@3,4-Dihydroxy-1-Phenylalanine Core-Shell Nanospheres Used for Cell Imaging. *J Phys Chem C* 2010;114:13010-6.
- [77] Fei B, Qian B, Yang Z, Wang R, Liu WC, Mak CL, Xin JH. Coating carbon nanotubes by spontaneous oxidative polymerization of dopamine. *Carbon* 2008;46:1795-7.
- [78] Long Y, Wu J, Wang H, Zhang X, Zhao N, Xu J. Rapid sintering of silver nanoparticles in an electrolyte solution at room temperature and its application to fabricate conductive silver films using polydopamine as adhesive layers. *J Mater Chem* 2011;21:4875-81.
- [79] Sureshkumar M, Lee P-N, Lee C-K. Stepwise assembly of multimetallic nanoparticles via self-polymerized polydopamine. *J Mater Chem* 2011;21:12316-20.
- [80] Wang W, Jiang Y, Liao Y, Tian M, Zou H, Zhang L. Fabrication of silver-coated silica microspheres through mussel-inspired surface functionalization. *J Colloid Interface Sci* 2011;358:567-74.

- [81] Zhang M, Zhang X, He X, Chen L, Zhang Y. Preparation and characterization of polydopamine-coated silver core/shell nanocables. *Chem Lett* 2010;39:552-3.
- [82] Wang W-C, Zhang A-N, Liu L, Tian M, Zhang L-Q. Dopamine-Induced Surface Functionalization for the Preparation of Al-Ag Bimetallic Microspheres. *J Electrochem Soc* 2011;158:228-33.
- [83] Sureshkumar M, Siswanto DY, Lee C-K. Magnetic antimicrobial nanocomposite based on bacterial cellulose and silver nanoparticles. *J Mater Chem* 2010;20:6948-55.
- [84] Xu H, Shi X, Ma H, Lv Y, Zhang L, Mao Z. The preparation and antibacterial effects of dopa-cotton/AgNPs. *Appl Surf Sci* 2011;257:6799-803.
- [85] Ma Y-r, Niu H-y, Zhang X-l, Cai Y-q. Colorimetric detection of copper ions in tap water during the synthesis of silver/dopamine nanoparticles. *Chem Commun* 2011;47:12643-5.
- [86] Taylor SW, Chase DB, Emptage MH, Nelson MJ, Waite JH. Ferric Ion Complexes of a DOPA-Containing Adhesive Protein from *Mytilus edulis*. *Inorg Chem* 1996;35:7572-7.
- [87] Holten-Andersen N, Mates TE, Toprak MS, Stucky GD, Zok FW, Waite JH. Metals and the Integrity of a Biological Coating: The Cuticle of Mussel Byssus. *Langmuir* 2009;25:3323-6.
- [88] Lee M, Ku SH, Ryu J, Park CB. Mussel-inspired functionalization of carbon nanotubes for hydroxyapatite mineralization. *J Mater Chem* 2010;20:8848-53.
- [89] Ryu J, Ku SH, Lee H, Park CB. Mussel-Inspired Polydopamine Coating as a Universal Route to Hydroxyapatite Crystallization. *Adv Funct Mater* 2010;20:2132-9.
- [90] Yan P, Wang J, Wang L, Liu B, Lei Z, Yang S. The in vitro biomineralization and cytocompatibility of polydopamine coated carbon nanotubes. *Appl Surf Sci* 2011;257:4849-55.
- [91] Kim S, Park CB. Dopamine-Induced Mineralization of Calcium Carbonate Vaterite Microspheres. *Langmuir* 2010;26:14730-6.
- [92] Kim S, Park CB. Mussel-inspired transformation of CaCO₃ to bone minerals. *Biomaterials* 2010;31:6628-34.
- [93] Kim S, Ko JW, Park CB. Bio-inspired mineralization of CO₂ gas to hollow CaCO₃ microspheres and bone hydroxyapatite/polymer composites. *J Mater Chem* 2011;21:11070-3.

- [94] Hu H, Yu B, Ye Q, Gu Y, Zhou F. Modification of carbon nanotubes with a nanothin polydopamine layer and polydimethylamino-ethyl methacrylate brushes. *Carbon* 2010;48:2347-53.
- [95] Wang W-C, Wang J, Liao Y, Zhang L, Cao B, Song G, She X. Surface initiated ATRP of acrylic acid on dopamine-functionalized AAO membranes. *J Appl Polym Sci* 2010;117:534-41.
- [96] Li CY, Wang WC, Xu FJ, Zhang LQ, Yang WT. Preparation of pH-sensitive membranes via dopamine-initiated atom transfer radical polymerization. *J Membr Sci* 2011;367:7-13.
- [97] Yang WJ, Cai T, Neoh K-G, Kang E-T, Dickinson GH, Teo SL-M, Rittschof D. Biomimetic Anchors for Antifouling and Antibacterial Polymer Brushes on Stainless Steel. *Langmuir* 2011;27:7065-76.
- [98] Shi Z, Neoh KG, Kang ET, Poh C, Wang W. Bacterial adhesion and osteoblast function on titanium with surface-grafted chitosan and immobilized RGD peptide. *J Biomed Mater Res Part A* 2008;86A:865-72.
- [99] Morris Todd A, Peterson Alexander W, Tarlov Michael J. Selective binding of RNase B glycoforms by polydopamine-immobilized concanavalin A. *Anal Chem* 2009;81:5413-20.
- [100] Tao C, Yang S, Zhang J, Wang J. Surface modification of diamond-like carbon films with protein via polydopamine inspired coatings. *Appl Surf Sci* 2009;256:294-7.
- [101] Zhu L-P, Yu J-Z, Xu Y-Y, Xi Z-Y, Zhu B-K. Surface modification of PVDF porous membranes via poly(DOPA) coating and heparin immobilization. *Colloids Surf B: Biointerfaces* 2009;69:152-5.
- [102] Biswas HS, Datta J, Chowdhury DP, Reddy AVR, Ghosh UC, Srivastava AK, Ray NR. Covalent Immobilization of Protein onto a functionalized Hydrogenated Diamond-like Carbon Substrate. *Langmuir* 2010;26:17413-8.
- [103] Jiang J-H, Zhu L-P, Li X-L, Xu Y-Y, Zhu B-K. Surface modification of polyethylene porous membranes based on the strong adhesion of polydopamine and covalent immobilization of heparin. *J Membr Sci* 2010;364:194-202.
- [104] Ku SH, Park CB. Human endothelial cell growth on mussel-inspired nanofiber scaffold for vascular tissue engineering. *Biomaterials* 2010;31:9431-7.

- [105] Poh CK, Shi Z, Lim TY, Neoh KG, Wang W. The effect of VEGF functionalization of titanium on endothelial cells in vitro. *Biomaterials* 2010;31:1578-85.
- [106] Wei Q, Zhang F, Li J, Li B, Zhao C. Oxidant-induced dopamine polymerization for multifunctional coatings. *Polym Chem* 2010;1:1430-3.
- [107] Kang K, Choi IS, Nam Y. A biofunctionalization scheme for neural interfaces using polydopamine polymer. *Biomaterials* 2011;32:6374-80.
- [108] Lai M, Cai K, Zhao L, Chen X, Hou Y, Yang Z. Surface Functionalization of TiO₂ Nanotubes with Bone Morphogenetic Protein 2 and Its Synergistic Effect on the Differentiation of Mesenchymal Stem Cells. *Biomacromolecules* 2011;12:1097-105.
- [109] Lynge ME, Ogaki R, Laursen AO, Lovmand J, Sutherland DS, Stadler B. Polydopamine/Liposome Coatings and Their Interaction with Myoblast Cells. *ACS Appl Mater Interfaces* 2011;3:2142-7.
- [110] Shin YM, Lee YB, Shin H. Time-dependent mussel-inspired functionalization of poly(L-lactide-co- ϵ -caprolactone) substrates for tunable cell behaviors. *Colloids Surf B: Biointerfaces* 2011;87:79-87.
- [111] Zhu L-P, Jiang J-H, Zhu B-K, Xu Y-Y. Immobilization of bovine serum albumin onto porous polyethylene membranes using strongly attached polydopamine as a spacer. *Colloids Surf B: Biointerfaces* 2011;86:111-8.
- [112] Wei Q, Li B, Yi N, Su B, Yin Z, Zhang F, Li J, Zhao C. Improving the blood compatibility of material surfaces via biomolecule-immobilized mussel-inspired coatings. *J Biomed Mater Res, Part A* 2011;96A:38-45.
- [113] McCloskey BD, Park HB, Ju H, Rowe BW, Miller DJ, Chun BJ, Kin K, Freeman BD. Influence of polydopamine deposition conditions on pure water flux and foulant adhesion resistance of reverse osmosis, ultrafiltration, and microfiltration membranes. *Polymer* 2010;51:3472-85.
- [114] Zeng R, Luo Z, Zhou D, Cao F, Wang Y. A novel PEG coating immobilized onto capillary through polydopamine coating for separation of proteins in CE. *Electrophoresis* 2010;31:3334-41.

- [115] Pop-Georgievski O, Popelka S, Houska M, Chvostova D, Proks V, Rypacek F. Poly(ethylene oxide) Layers Grafted to Dopamine-melanin Anchoring Layer: Stability and Resistance to Protein Adsorption. *Biomacromolecules* 2011;12:3232-42.
- [116] Tsai W-B, Chien C-Y, Thissen H, Lai J-Y. Dopamine-assisted immobilization of poly(ethylene imine) based polymers for control of cell-surface interactions. *Acta Biomater* 2011;7:2518-25.
- [117] Weng Y, Song Q, Zhou Y, Zhang L, Wang J, Chen J, Leng Y, Li S, Huang N. Immobilization of selenocystamine on TiO₂ surfaces for in situ catalytic generation of nitric oxide and potential application in intravascular stents. *Biomaterials* 2011;32:1253-63.
- [118] Paulo CSO, Vidal M, Ferreira LS. Antifungal Nanoparticles and Surfaces. *Biomacromolecules* 2010;11:2810-7.
- [119] Shalev T, Gopin A, Bauer M, Stark RW, Rahimipour S. Non-leaching antimicrobial surfaces through polydopamine bio-inspired coating of quaternary ammonium salts or an ultrashort antimicrobial lipopeptide. *J Mater Chem* 2012;22:2026-32.
- [120] Sureshkumar M, Lee C-K. Polydopamine coated magnetic-chitin (MCT) particles as a new matrix for enzyme immobilization. *Carbohydr Polym* 2011;84:775-80.
- [121] Fu Y, Li P, Xie Q, Xu X, Lei L, Chen C, Zou C, Deng W, Yao S. One-pot preparation of polymer-enzyme-metallic nanoparticle composite films for high-performance biosensing of glucose and galactose. *Adv Funct Mater* 2009;19:1784-91.
- [122] Fu Y, Li P, Bu L, Wang T, Xie Q, Xu X, Lei L, Zou C, Yao S. Chemical/Biochemical Preparation of New Polymeric Bionanocomposites with Enzyme Labels Immobilized at High Load and Activity for High-Performance Electrochemical Immunoassay. *J Phys Chem C* 2010;114:1472-80.
- [123] Fu Y, Li P, Wang T, Bu L, Xie Q, Xu X, Lei L, Zou C, Chen J, Yao S. Novel polymeric bionanocomposites with catalytic Pt nanoparticles label immobilized for high performance amperometric immunoassay. *Biosens Bioelectron* 2010;25:1699-704.
- [124] Wan Y, Zhang D, Wang Y, Qi P, Hou B. Direct immobilisation of antibodies on a bioinspired architecture as a sensing platform. *Biosens Bioelectron* 2011;26:2595-600.

- [125] Wang G, Huang H, Zhang G, Zhang X, Fang B, Wang L. Dual amplification strategy for fabrication of highly sensitive Interleukin-6 amperometric immunosensor based on poly-dopamine. *Langmuir* 2011;27:1224-31.
- [126] Kang SM, Rho J, Choi IS, Messersmith PB, Lee H. Norepinephrine: Material-Independent, Multifunctional Surface Modification Reagent. *J Am Chem Soc* 2009;131:13224-5.
- [127] Dechy-Cabaret O, Martin-Vaca B, Bourissou D. Controlled Ring-Opening Polymerization of Lactide and Glycolide. *Chem Rev* 2004;104:6147-76.
- [128] Kobayashi S, Uyama H, Kimura S. Enzymatic polymerization. *Chem Rev* 2001;101:3793-818.
- [129] Kobayashi S, Makino A. Enzymatic Polymer Synthesis: An Opportunity for Green Polymer Chemistry. *Chem Rev* 2009;109:5288-353.
- [130] Ward G, Parales RE, Dosoretz CG. Biocatalytic Synthesis of Polycatechols from Toxic Aromatic Compounds. *Environ Sci Technol* 2004;38:4753-7.
- [131] Nabid MR, Zamiraei Z, Sedghi R, Nazari S. Synthesis and characterization of poly(catechol) catalyzed by porphyrin and enzyme. *Polym Bull* 2010;64:855-65.
- [132] Mejias L, Reihmann MH, Sepulveda-Boza S, Ritter H. New polymers from natural phenols using horseradish or soybean peroxidase. *Macromol Biosci* 2002;2:24-32.
- [133] Kurisawa M, Chung JE, Kim YJ, Uyama H, Kobayashi S. Amplification of antioxidant activity and xanthine oxidase inhibition of catechin by enzymatic polymerization. *Biomacromolecules* 2003;4:469-71.
- [134] Xu P, Uyama H, Whitten JE, Kobayashi S, Kaplan DL. Peroxidase-Catalyzed in Situ Polymerization of Surface Orientated Caffeic Acid. *J Am Chem Soc* 2005;127:11745-53.
- [135] Foppoli C, Coccia R, Cini C, Rosei MA. Catecholamines oxidation by xanthine oxidase. *Biochim Biophys Acta Gen Subj* 1997;1334:200-6.
- [136] Aktas N, Sahiner N, Kantoglu O, Salih B, Tanyolac A. Biosynthesis and Characterization of Laccase Catalyzed Poly(Catechol). *J Polym Environ* 2003;11:123-8.
- [137] Kurisawa M, Chung JE, Uyama H, Kobayashi S. Laccase-catalyzed synthesis and antioxidant property of poly(catechin). *Macromol Biosci* 2003;3:758-64.

- [138] Kurisawa M, Chung JE, Uyama H, Kobayashi S. Enzymatic Synthesis and Antioxidant Properties of Poly(rutin). *Biomacromolecules* 2003;4:1394-9.
- [139] Desentis-Mendoza RM, Hernandez-Sanchez H, Moreno A, Rojas del C E, Chel-Guerrero L, Tamariz J, Jaramillo-Flores ME. Enzymatic Polymerization of Phenolic Compounds Using Laccase and Tyrosinase from *Ustilago maydis*. *Biomacromolecules* 2006;7:1845-54.
- [140] Casassa EZ, Sarquis AM, Van Dyke CH. The gelation of polyvinyl alcohol with borax. A novel class participation experiment involving the preparation and properties of a "slime". *J Chem Educ* 1986;63:57-60.
- [141] Liu Z, Hu B-H, Messersmith PB. Convenient synthesis of acetonide-protected 3,4-dihydroxyphenylalanine (DOPA) for Fmoc solid-phase peptide synthesis. *Tetrahedron Lett* 2008;49:5519-21.
- [142] Xu C, Xu K, Gu H, Zheng R, Liu H, Zhang X, Guo Z, Xu B. Dopamine as a robust anchor to immobilize functional molecules on the iron oxide shell of magnetic nanoparticles. *J Am Chem Soc* 2004;126:9938-9.
- [143] Liu Y, Li K. Chemical modification of soy protein for wood adhesives. *Macromol Rapid Commun* 2002;23:739-42.
- [144] Zhang C, Li K, Simonsen J. A novel wood-binding domain of a wood-plastic coupling agent: development and characterization. *J Appl Polym Sci* 2003;89:1078-84.
- [145] Haller CM, Buerzle W, Brubaker CE, Messersmith PB, Mazza E, Ochsenbein-Koelble N, Zimmermann R, Ehrbar M. Mussel-mimetic tissue adhesive for fetal membrane repair: a standardized ex vivo evaluation using elastomeric membranes. *Prenatal Diagn* 2011;31:654-60.
- [146] Westwood G, Horton TN, Wilker JJ. Simplified Polymer Mimics of Cross-Linking Adhesive Proteins. *Macromolecules* 2007;40:3960-4.
- [147] White JD, Wilker JJ. Underwater Bonding with Charged Polymer Mimics of Marine Mussel Adhesive Proteins. *Macromolecules* 2011;44:5085-8.
- [148] Lee H, Lee BP, Messersmith PB. A reversible wet/dry adhesive inspired by mussels and geckos. *Nature* 2007;448:338-41.

- [149] Charlot A, Sciannamea V, Lenoir S, Faure E, Jerome R, Jerome C, Van De Weerd C, Martial J, Archambeau C, Willet N, Duwez A-S, Fustin C-A, Detrembleur C. All-in-one strategy for the fabrication of antimicrobial biomimetic films on stainless steel. *J Mater Chem* 2009;19:4117-25.
- [150] Moad G, Solomon D. *The Chemistry of Radical Polymerization*. Oxford, Elsevier; 2006. p. 639
- [151] Karasch MS, Kawahara F, Nudenberg W. The mechanism of action of inhibitors in free radical initiated polymerizations at low temperatures. *J Org Chem* 1954;19:1977-90.
- [152] Glass P, Chung H, Washburn NR, Sitti M. Enhanced Reversible Adhesion of Dopamine Methacrylamide-Coated Elastomer Microfibrillar Structures under Wet Conditions. *Langmuir* 2009;25:6607-12.
- [153] Shao H, Bachus KN, Stewart RJ. A water-borne adhesive modeled after the sandcastle glue of *P. californica*. *Macromol Biosci* 2009;9:464-71.
- [154] Shao H, Stewart RJ. Biomimetic Underwater Adhesives with Environmentally Triggered Setting Mechanisms. *Adv Mater* 2010;22:729-33.
- [155] Shao H, Weerasekare GM, Stewart RJ. Controlled curing of adhesive complex coacervates with reversible periodate carbohydrate complexes. *J Biomed Mater Res Part A* 2011;97A:46-51.
- [156] Wang X, Ye Q, Liu J, Liu X, Zhou F. Low surface energy surfaces from self-assembly of perfluoropolymer with sticky functional groups. *J Colloid Interface Sci* 2010;351:261-6.
- [157] Ham HO, Liu Z, Lau KHA, Lee H, Messersmith PB. Facile DNA Immobilization on Surfaces through a Catecholamine Polymer. *Angew Chem Int Ed* 2011;50:732-6.
- [158] Wang X, Ye Q, Gao T, Liu J, Zhou F. Self-Assembly of Catecholic Macroinitiator on Various Substrates and Surface-Initiated Polymerization. *Langmuir* 2012;28:2574-81.
- [159] Glass P, Chung H, Washburn NR, Sitti M. Enhanced Wet Adhesion and Shear of Elastomeric Micro-Fiber Arrays with Mushroom Tip Geometry and a Photopolymerized p(DMA-co-MEA) Tip Coating. *Langmuir* 2010;26:17357-62.
- [160] Chung H-Y, Glass P, Pothen JM, Sitti M, Washburn NR. Enhanced Adhesion of Dopamine Methacrylamide Elastomers via Viscoelasticity Tuning. *Biomacromolecules* 2011;12:342-7.

- [161] Han H, Wu J, Avery CW, Mizutani M, Jiang X, Kamigaito M, Chen Z, Xi C, Kuroda K. Immobilization of Amphiphilic Polycations by Catechol Functionality for Antimicrobial Coatings. *Langmuir* 2011;27:4010-9.
- [162] Xue X, Pasparakis G, Halliday N, Winzer K, Howdle SM, Cramphorn CJ, Cameron NR, Gardner PM, Davis BG, Fernandez-Trillo F, Alexander C. Synthetic Polymers for Simultaneous Bacterial Sequestration and Quorum Sense Interference. *Angew Chem Int Ed* 2011;50:9852-6.
- [163] Van De Weerd C, Detrembleur C, Charlot A, Jerome R, Vreuls C, Zocchi G. Multifunctional polyelectrolyte coatings. *PCT Int Appl. Wo* 2009/147007. 2009. pp. 90 pp
- [164] Falentin-Daudre C, Faure E, Svaldo Lanero T, Farina F, Jerome C, Van de Weerd C, Martial J, Duwez A-S, Detrembleur C. Antibacterial polyelectrolyte micelles for coating stainless steel. *Langmuir* 2012;doi.org/10.1021/la3003965.
- [165] Vreuls C, Zocchi G, Garitte G, Archambeau C, Martial J, Van de Weerd C. Biomolecules in multilayer film for antimicrobial and easy-cleaning stainless steel surface applications. *Biofouling* 2010;26:645-56.
- [166] Faure E, Halusiak E, Farina F, Giambianco N, Motte C, Poelman M, Archambeau C, Van De Weerd C, Martial J, Jerome C, Duwez A-S, Detrembleur C. Clay and DOPA Containing Polyelectrolyte Multilayer Film for Imparting Anticorrosion Properties to Galvanized Steel. *Langmuir* 2012;28:2971-8.
- [167] Yamamoto H, Hayakawa T. Synthesis of sequential polypeptides containing L- β -3,4-dihydroxyphenyl- α -alanine (DOPA) and L-glutamic acid. *Biopolymers* 1979;18:3067-76.
- [168] Yamamoto H, Hayakawa T. Synthesis of sequential polypeptides containing L- β -(3,4-dihydroxyphenyl)- α -alanine (DOPA) and L-lysine. *Biopolymers* 1982;21:1137-51.
- [169] Statz A, Finlay J, Dalsin J, Callow M, Callow JA, Messersmith PB. Algal antifouling and fouling-release properties of metal surfaces coated with a polymer inspired by marine mussels. *Biofouling* 2006;22:391-9.
- [170] Ko R, Cadieux Peter A, Dalsin Jeffrey L, Lee Bruce P, Elwood Chelsea N, Razvi H. First prize: Novel uropathogen-resistant coatings inspired by marine mussels. *J Endourol* 2008;22:1153-60.

- [171] Pechey A, Elwood Chelsea N, Wignall Geoffrey R, Dalsin Jeffrey L, Lee Bruce P, Vanjcek M, Welch I, Ko R, Razvi H, Cadieux Peter A. Anti-adhesive coating and clearance of device associated uropathogenic Escherichia coli cystitis. *J Urol* 2009;182:1628-36.
- [172] Deming TJ. Synthetic polypeptides for biomedical applications. *Prog Polym Sci* 2007;32:858-75.
- [173] Hu BH, Messersmith PB. Protection of 3,4-dihydroxyphenylalanine (DOPA) for Fmoc solid-phase peptide synthesis. *Tetrahedron Lett* 2000;41:5795-8.
- [174] Sever MJ, Wilker JJ. Synthesis of peptides containing DOPA (3,4-dihydroxyphenylalanine). *Tetrahedron* 2001;57:6139-46.
- [175] Statz AR, Meagher RJ, Barron AE, Messersmith PB. New peptidomimetic polymers for antifouling surfaces. *J Am Chem Soc* 2005;127:7972-3.
- [176] Samyn P, Ruehe J, Biesalski M. Polymerizable Biomimetic Vesicles with Controlled Local Presentation of Adhesive Functional DOPA Groups. *Langmuir* 2010;26:8573-81.
- [177] Black KCL, Liu Z, Messersmith PB. Catechol redox induced formation of metal core-polymer shell nanoparticles. *Chem Mater* 2011;23:1130-5.
- [178] Kricheldorf HR. α -Amino acid N-carboxy anhydrides and related heterocycles: syntheses, properties, peptide synthesis, polymerization. New York 1987. p. 213 pp
- [179] Yu M, Deming TJ. Synthetic Polypeptide Mimics of Marine Adhesives. *Macromolecules* 1998;31:4739-45.
- [180] Wang J, Liu C, Lu X, Yin M. Co-polypeptides of 3,4-dihydroxyphenylalanine and -lysine to mimic marine adhesive protein. *Biomaterials* 2007;28:3456-68.
- [181] Yin M, Yuan Y, Liu C, Wang J. Development of mussel adhesive polypeptide mimics coating for in-situ inducing re-endothelialization of intravascular stent devices. *Biomaterials* 2009;30:2764-73.
- [182] Holowka EP, Deming TJ. Synthesis and Crosslinking of L-DOPA Containing Polypeptide Vesicles. *Macromol Biosci* 2010;10:496-502.

- [183] Ling D, Park W, Park YI, Lee N, Li F, Song C, Yang S-G, Choi SH, Na K, Hyeon T. Multiple-Interaction Ligands Inspired by Mussel Adhesive Protein: Synthesis of Highly Stable and Biocompatible Nanoparticles. *Angew Chem Int Ed* 2011;50:11360-5.
- [184] Lee BP, Chao C-Y, Nunalee FN, Motan E, Shull KR, Messersmith PB. Rapid Gel Formation and Adhesion in Photocurable and Biodegradable Block Copolymers with High DOPA Content. *Macromolecules* 2006;39:1740-8.
- [185] Gunawan RC, King JA, Lee BP, Messersmith PB, Miller WM. Surface Presentation of Bioactive Ligands in a Nonadhesive Background Using DOPA-Tethered Biotinylated Poly(ethylene glycol). *Langmuir* 2007;23:10635-43.
- [186] Podsiadlo P, Liu Z, Paterson D, Messersmith PB, Kotov NA. Fusion of seashell nacre and marine bioadhesive analogs: high-strength nanocomposite by layer-by-layer assembly of clay and L-3,4-dihydroxyphenylalanine polymer. *Adv Mater* 2007;19:949-55.
- [187] Monahan J, Wilker JJ. Specificity of metal ion cross-linking in marine mussel adhesives. *Chem Commun* 2003:1672-3.
- [188] Sever MJ, Weisser JT, Monahan J, Srinivasan S, Wilker JJ. Metal-mediated cross-linking in the generation of a marine-mussel adhesive. *Angew Chem Int Ed* 2004;43:448-50.
- [189] Harrington MJ, Masic A, Holten-Andersen N, Waite JH, Fratzl P. Iron-Clad Fibers: A Metal-Based Biological Strategy for Hard Flexible Coatings. *Science* 2010;328:216-20.
- [190] Wilker JJ. Marine bioinorganic materials: Mussels pumping iron. *Curr Opin Chem Biol* 2010;14:276-83.
- [191] Zeng H, Hwang Dong S, Israelachvili Jacob N, Waite JH. Strong reversible Fe³⁺-mediated bridging between dopa-containing protein films in water. *Proc Natl Acad Sci USA* 2010;107:12850-3.
- [192] Holten-Andersen N, Harrington Matthew J, Birkedal H, Lee Bruce P, Messersmith Phillip B, Lee Ka Yee C, Waite JH. pH-induced metal-ligand cross-links inspired by mussel yield self-healing polymer networks with near-covalent elastic moduli. *Proc Natl Acad Sci USA* 2011;108:2651-5.
- [193] Zhang F, Liu S, Zhang Y, Xu J, Chi Z. A simplified approach to achieve gecko-mimic nano-structural adhesives by a simple polymer. *Int J Adhes Adhes* 2011;31:583-6.

- [194] Guvendiren M, Messersmith PB, Shull KR. Self-Assembly and Adhesion of DOPA-Modified Methacrylic Triblock Hydrogels. *Biomacromolecules* 2008;9:122-8.
- [195] Wu J, Zhang L, Wang Y, Long Y, Gao H, Zhang X, Zhao N, Cai Y, Xu J. Mussel-Inspired Chemistry for Robust and Surface-Modifiable Multilayer Films. *Langmuir* 2011;27:13684-91.
- [196] Min Y, Hammond PT. Catechol-Modified Polyions in Layer-by-Layer Assembly to Enhance Stability and Sustain Release of Biomolecules: A Bioinspired Approach. *Chem Mater* 2011;23:5349-57.
- [197] Tahir MN, Eberhardt M, Theato P, Faiss S, Janshoff A, Gorelik T, Kolb U, Tremel W. Reactive polymers: a versatile toolbox for the immobilization of functional molecules on TiO₂ nanoparticles. *Angew Chem Int Ed* 2006;45:908-12.
- [198] Tahir MN, Zink N, Eberhardt M, Therese HA, Kolb U, Theato P, Tremel W. Overcoming the insolubility of molybdenum disulfide nanoparticles through a high degree of sidewall functionalization using polymeric chelating ligands. *Angew Chem Int Ed* 2006;45:4809-15.
- [199] Shukoor MI, Natalio F, Therese HA, Tahir MN, Ksenofontov V, Panthoefer M, Eberhardt M, Theato P, Schroeder HC, Mueller WEG, Tremel W. Fabrication of a Silica Coating on Magnetic γ -Fe₂O₃ Nanoparticles by an Immobilized Enzyme. *Chem Mater* 2008;20:3567-73.
- [200] Shukoor MI, Natalio F, Metz N, Glube N, Tahir MN, Therese HA, Ksenofontov V, Theato P, Langguth P, Boissel J-P, Schroeder HC, Mueller WEG, Tremel W. dsRNA-functionalized multifunctional γ -Fe₂O₃ nanocrystals: a tool for targeting cell surface receptors. *Angew Chem Int Ed* 2008;47:4748-52.
- [201] Shukoor MI, Natalio F, Tahir MN, Wiens M, Tarantola M, Therese HA, Barz M, Weber S, Terekhov M, Schroeder HC, Mueller WEG, Janshoff A, Theato P, Zentel R, Schreiber LM, Tremel W. Pathogen-mimicking MnO nanoparticles for selective activation of TLR9 pathway and imaging of cancer cells. *Adv Funct Mater* 2009;19:3717-25.
- [202] Meuer S, Oberle P, Theato P, Tremel W, Zentel R. Liquid crystalline phases from polymer-functionalized TiO₂ nanorods. *Adv Mater* 2007;19:2073-8.

- [203] Zorn M, Meuer S, Tahir MN, Khalavka Y, Soennichsen C, Tremel W, Zentel R. Liquid crystalline phases from polymer functionalized semiconducting nanorods. *J Mater Chem* 2008;18:3050-8.
- [204] Zorn M, Tahir MN, Bergmann B, Tremel W, Grigoriadis C, Floudas G, Zentel R. Orientation and Dynamics of ZnO Nanorod Liquid Crystals in Electric Fields. *Macromol Rapid Commun* 2010;31:1101-7.
- [205] Xu LQ, Jiang H, Neoh K-G, Kang E-T, Fu GD. Poly(dopamine acrylamide)-co-poly(propargyl acrylamide)-modified titanium surfaces for click' functionalization. *Polym Chem* 2012;3:920-7.
- [206] Ochs CJ, Hong T, Such GK, Cui J, Postma A, Caruso F. Dopamine-Mediated Continuous Assembly of Biodegradable Capsules. *Chem Mater* 2011;23:3141-3.
- [207] Lee H, Lee KD, Pyo KB, Park SY, Lee H. Catechol-Grafted Poly(ethylene glycol) for PEGylation on Versatile Substrates. *Langmuir* 2010;26:3790-3.
- [208] Kim TG, Lee H, Jang Y, Park TG. Controlled Release of Paclitaxel from Heparinized Metal Stent Fabricated by Layer-by-Layer Assembly of Polylysine and Hyaluronic Acid-g-Poly(lactic-co-glycolic acid) Micelles Encapsulating Paclitaxel. *Biomacromolecules* 2009;10:1532-9.
- [209] Sun I-C, Eun D-K, Na JH, Lee S, Kim I-J, Youn I-C, Ko C-Y, Kim H-S, Lim D, Choi K, Messersmith PB, Park TG, Kim SY, Kwon IC, Kim K, Ahn C-H. Heparin-Coated Gold Nanoparticles for Liver-Specific CT Imaging. *Chem--Eur J* 2009;15:13341-7.
- [210] Lee Y, Lee H, Kim YB, Kim J, Hyeon T, Park H, Messersmith PB, Park TG. Bioinspired surface immobilization of hyaluronic acid on monodisperse magnetite nanocrystals for targeted cancer imaging. *Adv Mater* 2008;20:4154-7.
- [211] Lee H, Lee K, Kim I-K, Park TG. Fluorescent gold nanoprobe sensitive to intracellular reactive oxygen species. *Adv Funct Mater* 2009;19:1884-90.
- [212] Lee Y, Lee H, Messersmith PB, Park TG. A Bioinspired Polymeric Template for 1D Assembly of Metallic Nanoparticles, Semiconductor Quantum Dots, and Magnetic Nanoparticles. *Macromol Rapid Commun* 2010;31:2109-14.

- [213] Lee Y, Chung HJ, Yeo S, Ahn C-H, Lee H, Messersmith PB, Park TG. Thermo-sensitive, injectable, and tissue adhesive sol-gel transition hyaluronic acid/pluronic composite hydrogels prepared from bio-inspired catechol-thiol reaction. *Soft Matter* 2010;6:977-83.
- [214] Saxer S, Portmann C, Tosatti S, Gademann K, Zurcher S, Textor M. Surface Assembly of Catechol-Functionalized Poly(L-lysine)-graft-poly(ethylene glycol) Copolymer on Titanium Exploiting Combined Electrostatically Driven Self-Organization and Biomimetic Strong Adhesion. *Macromolecules* 2010;43:1050-60.
- [215] Ryu JH, Lee Y, Kong WH, Kim TG, Park TG, Lee H. Catechol-Functionalized Chitosan/Pluronic Hydrogels for Tissue Adhesives and Hemostatic Materials. *Biomacromolecules* 2011;12:2653-9.
- [216] Hu X, Neoh K-G, Shi Z, Kang E-T, Poh C, Wang W. An in vitro assessment of titanium functionalized with polysaccharides conjugated with vascular endothelial growth factor for enhanced osseointegration and inhibition of bacterial adhesion. *Biomaterials* 2010;31:8854-63.
- [217] Lee H, Lee Y, Statz AR, Rho J, Park TG, Messersmith PB. Substrate-independent layer-by-layer assembly by using mussel-adhesive-inspired polymers. *Adv Mater* 2008;20:1619-23.
- [218] Ryu S, Lee Y, Hwang J-W, Hong S, Kim C, Park TG, Lee H, Hong SH. High-Strength Carbon Nanotube Fibers Fabricated by Infiltration and Curing of Mussel-Inspired Catecholamine Polymer. *Adv Mater* 2011;23:1971-5.
- [219] Murphy JL, Vollenweider L, Xu F, Lee BP. Adhesive Performance of Biomimetic Adhesive-Coated Biologic Scaffolds. *Biomacromolecules* 2010;11:2976-84.
- [220] Brodie M, Vollenweider L, Murphy JL, Xu F, Lyman A, Lew WD, Lee BP. Biomechanical properties of Achilles tendon repair augmented with a bioadhesive-coated scaffold. *Biomed Mater* 2011;6:015014/1-/8.
- [221] Kim E, Liu Y, Shi X-W, Yang X, Bentley WE, Payne GF. Biomimetic Approach to Confer Redox Activity to Thin Chitosan Films. *Adv Funct Mater* 2010;20:2683-94.

- [222] Kim E, Liu Y, Baker CJ, Owens R, Xiao S, Bentley WE, Payne GF. Redox-Cycling and H₂O₂ Generation by Fabricated Catecholic Films in the Absence of Enzymes. *Biomacromolecules* 2011;12:880-8.
- [223] Marumo K, Waite JH. Optimization of hydroxylation of tyrosine and tyrosine-containing peptides by mushroom tyrosinase. *Biochim Biophys Acta, Protein Struct Mol Enzymol* 1986;872:98-103.
- [224] Yamamoto H, Ohkawa K. Synthesis of adhesive protein from the vitellaria of the liver fluke *Fasciola hepatica*. *Amino Acids* 1993;5:71-5.
- [225] Yamamoto H, Tatehata H. Oxidation of synthetic precursors of adhesive proteins from mytilid bivalves using tyrosinase. *J Mar Biotechnol* 1995;2:95-100.
- [226] Kuboe Y, Tonegawa H, Ohkawa K, Yamamoto H. Quinone Cross-Linked Polysaccharide Hybrid Fiber. *Biomacromolecules* 2004;5:348-57.
- [227] Jus S, Kokol V, Guebitz GM. Tyrosinase-catalysed coupling of functional molecules onto protein fibers. *Enzyme Microb Technol* 2008;42:535-42.
- [228] Uyama H, Kobayashi S. Enzymatic synthesis and properties of polymers from polyphenols. *Adv Polym Sci* 2006;194:51-67.
- [229] Hong R, Fischer NO, Emrick T, Rotello VM. Surface PEGylation and Ligand Exchange Chemistry of FePt Nanoparticles for Biological Applications. *Chem Mater* 2005;17:4617-21.
- [230] Xie J, Xu C, Kohler N, Hou Y, Sun S. Controlled PEGylation of monodisperse Fe₃O₄ nanoparticles for reduced non-specific uptake by macrophage cells. *Adv Mater* 2007;19:3163-6.
- [231] Somaskandan K, Veres T, Niewczas M, Simard B. Surface protected and modified iron based core-shell nanoparticles for biological applications. *New J Chem* 2008;32:201-9.
- [232] Wu H, Zhu H, Zhuang J, Yang S, Liu C, Cao YC. Water-soluble nanocrystals through dual-interaction ligands. *Angew Chem Int Ed* 2008;47:3730-4.
- [233] Xu C, Xie J, Ho D, Wang C, Kohler N, Walsh EG, Morgan JR, Chin YE, Sun S. Au-Fe₃O₄ dumbbell nanoparticles as dual-functional probes. *Angew Chem Int Ed* 2008;47:173-6.

- [234] Zurcher S, Wackerlin D, Bethuel Y, Malisova B, Textor M, Tosatti S, Gademann K. Biomimetic surface modifications based on the cyanobacterial iron chelator anachelin. *J Am Chem Soc* 2006;128:1064-5.
- [235] Wach J-Y, Bonazzi S, Gademann K. Antimicrobial surfaces through natural product hybrids. *Angew Chem Int Ed* 2008;47:7123-6.
- [236] Wach J-Y, Malisova B, Bonazzi S, Tosatti S, Textor M, Zurcher S, Gademann K. Protein-resistant surfaces through mild dopamine surface functionalization. *Chem--Eur J* 2008;14:10579-84.
- [237] Amstad E, Gillich T, Bilecka I, Textor M, Reimhult E. Ultrastable Iron Oxide Nanoparticle Colloidal Suspensions using Dispersants with Catechol-Derived Anchor Groups. *Nano Lett* 2009;9:4042-8.
- [238] Malisova B, Tosatti S, Textor M, Gademann K, Zurcher S. Poly(ethylene glycol) Adlayers Immobilized to Metal Oxide Substrates Through Catechol Derivatives: Influence of Assembly Conditions on Formation and Stability. *Langmuir* 2010;26:4018-26.
- [239] Shafiq Z, Cui J, Pastor-Perez L, San Miguel V, Gropeanu RA, Serrano C, del Campo A. Bioinspired Underwater Bonding and Debonding on Demand. *Angew Chem Int Ed* 2012;51:4332-5.
- [240] Su J, Chen F, Cryns VL, Messersmith PB. Catechol Polymers for pH-Responsive, Targeted Drug Delivery to Cancer Cells. *J Am Chem Soc* 2011;133:11850-3.
- [241] Hu B-H, Messersmith PB. Rational Design of Transglutaminase Substrate Peptides for Rapid Enzymatic Formation of Hydrogels. *J Am Chem Soc* 2003;125:14298-9.
- [242] Catron ND, Lee H, Messersmith PB. Enhancement of poly(ethylene glycol) mucoadsorption by biomimetic end group functionalization. *Biointerphases* 2006;1:134-41.
- [243] Burke SA, Ritter-Jones M, Lee BP, Messersmith PB. Thermal gelation and tissue adhesion of biomimetic hydrogels. *Biomed Mater* 2007;2:203-10.
- [244] Brubaker CE, Kissler H, Wang L-J, Kaufman DB, Messersmith PB. Biological performance of mussel-inspired adhesive in extrahepatic islet transplantation. *Biomaterials* 2010;31:420-7.
- [245] Lee BP, Dalsin JL, Messersmith PB. Synthesis and Gelation of DOPA-Modified Poly(ethylene glycol) Hydrogels. *Biomacromolecules* 2002;3:1038-47.

- [246] Zhu R, Jiang W, Pu Y, Luo K, Wu Y, He B, Gu Z. Functionalization of magnetic nanoparticles with peptide dendrimers. *J Mater Chem* 2011;21:5464-74.
- [247] He L, Fullenkamp DE, Rivera JG, Messersmith PB. pH responsive self-healing hydrogels formed by boronate-catechol complexation. *Chem Commun* 2011;47:7497-9.
- [248] Xie J, Xu C, Xu Z, Hou Y, Young KL, Wang SX, Pourmond N, Sun S. Linking Hydrophilic Macromolecules to Monodisperse Magnetite (Fe₃O₄) Nanoparticles via Trichloro-s-triazine. *Chem Mater* 2006;18:5401-3.
- [249] Brubaker CE, Messersmith PB. Enzymatically Degradable Mussel-Inspired Adhesive Hydrogel. *Biomacromolecules* 2011;12:4326-34.
- [250] Rajh T, Saponjic Z, Liu J, Dimitrijevic NM, Scherer NF, Vega-Arroyo M, Zapol P, Curtiss LA, Thurnauer MC. Charge Transfer Across the Nanocrystalline-DNA Interface: Probing DNA Recognition. *Nano Lett* 2004;4:1017-23.
- [251] Huang K, Lee BP, Ingram DR, Messersmith PB. Synthesis and Characterization of Self-Assembling Block Copolymers Containing Bioadhesive End Groups. *Biomacromolecules* 2002;3:397-406.
- [252] Matyjaszewski K, Xia J. Atom Transfer Radical Polymerization. *Chem Rev* 2001;101:2921-90.
- [253] Siegwart DJ, Oh JK, Matyjaszewski K. ATRP in the design of functional materials for biomedical applications. *Prog Polym Sci* 2012;37:18-37.
- [254] Ouchi M, Terashima T, Sawamoto M. Transition Metal-Catalyzed Living Radical Polymerization: Toward Perfection in Catalysis and Precision Polymer Synthesis. *Chem Rev* 2009;109:4963-5050.
- [255] Moad G, Rizzardo E, Thang SH. Radical addition-fragmentation chemistry in polymer synthesis. *Polymer* 2008;49:1079-131.
- [256] Moad G, Rizzardo E, Thang SH. Reversible addition fragmentation chain transfer (RAFT) polymerization. *Mater Matters* 2010;5:2-8.
- [257] Barner-Kowollik C, editor. *Handbook of RAFT Polymerization*. Wiley VCH ed. Weinheim 2008. p. 543 pp

- [258] Li G, Cheng G, Xue H, Chen S, Zhang F, Jiang S. Ultra low fouling zwitterionic polymers with a biomimetic adhesive group. *Biomaterials* 2008;29:4592-7.
- [259] Gao C, Li G, Xue H, Yang W, Zhang F, Jiang S. Functionalizable and ultra-low fouling zwitterionic surfaces via adhesive mussel mimetic linkages. *Biomaterials* 2010;31:1486-92.
- [260] Li G, Xue H, Gao C, Zhang F, Jiang S. Nonfouling Polyampholytes from an Ion-Pair Comonomer with Biomimetic Adhesive Groups. *Macromolecules* 2010;43:14-6.
- [261] Chanana M, Jahn S, Georgieva R, Lutz J-F, Baumler H, Wang D. Fabrication of Colloidal Stable, Thermosensitive, and Biocompatible Magnetite Nanoparticles and Study of Their Reversible Agglomeration in Aqueous Milieu. *Chem Mater* 2009;21:1906-14.
- [262] Zobrist C, Sobocinski J, Lyskawa J, Fournier D, Miri V, Traisnel M, Jimenez M, Woisel P. Functionalization of Titanium Surfaces with Polymer Brushes Prepared from a Biomimetic RAFT Agent. *Macromolecules* 2011;44:5883-92.
- [263] Brault ND, Gao C, Xue H, Piliarik M, Homola J, Jiang S, Yu Q. Ultra-low fouling and functionalizable zwitterionic coatings grafted onto SiO₂ via a biomimetic adhesive group for sensing and detection in complex media. *Biosens Bioelectron* 2010;25:2276-82.
- [264] Stefaniu C, Chanana M, Wang D, Novikov DV, Brezesinski G, Mohwald H. Langmuir and Gibbs Magnetite NP Layers at the Air/Water Interface. *Langmuir* 2011;27:1192-9.
- [265] Barras A, Lyskawa J, Szunerits S, Woisel P, Boukherroub R. Direct Functionalization of Nanodiamond Particles Using Dopamine Derivatives. *Langmuir* 2011;27:12451-7.
- [266] Golas PL, Matyjaszewski K. Marrying click chemistry with polymerization: expanding the scope of polymeric materials. *Chem Soc Rev* 2010;39:1338-54.
- [267] Kolb HC, Finn MG, Sharpless KB. Click chemistry: diverse chemical function from a few good reactions. *Angew Chem Int Ed* 2001;40:2004-21.
- [268] Goldmann AS, Schoedel C, Walther A, Yuan J, Loos K, Mueller AHE. Biomimetic Mussel Adhesive Inspired Clickable Anchors Applied to the Functionalization of Fe₃O₄ Nanoparticles. *Macromol Rapid Commun* 2010;31:1608-15.

- [269] Watson MA, Lyskawa J, Zobrist C, Fournier D, Jimenez M, Traisnel M, Gengembre L, Woisel P. A "Clickable" Titanium Surface Platform. *Langmuir* 2010;26:15920-4.
- [270] Fan X, Lin L, Messersmith PB. Cell Fouling Resistance of Polymer Brushes Grafted from Ti Substrates by Surface-Initiated Polymerization: Effect of Ethylene Glycol Side Chain Length. *Biomacromolecules* 2006;7:2443-8.
- [271] Fan X, Lin L, Messersmith PB. Surface-initiated polymerization from TiO₂ nanoparticle surfaces through a biomimetic initiator: a new route toward polymer-matrix nanocomposites. *Compos Sci Technol* 2006;66:1198-204.
- [272] Hamming LM, Fan XW, Messersmith PB, Brinson LC. Mimicking mussel adhesion to improve interfacial properties in composites. *Compos Sci Technol* 2008;68:2042-8.
- [273] Yuan S, Wan D, Liang B, Pehkonen SO, Ting YP, Neoh KG, Kang ET. Lysozyme-Coupled Poly(poly(ethylene glycol) methacrylate)-Stainless Steel Hybrids and Their Antifouling and Antibacterial Surfaces. *Langmuir* 2011;27:2761-74.
- [274] Li G, Xue H, Cheng G, Chen S, Zhang F, Jiang S. Ultralow Fouling Zwitterionic Polymers Grafted from Surfaces Covered with an Initiator via an Adhesive Mussel Mimetic Linkage. *J Phys Chem B* 2008;112:15269-74.
- [275] Ye Q, Wang X, Hu H, Wang D, Li S, Zhou F. Polyelectrolyte Brush Templated Multiple Loading of Pd Nanoparticles onto TiO₂ Nanowires via Regenerative Counterion Exchange-Reduction. *J Phys Chem C* 2009;113:7677-83.
- [276] Zhu B, Edmondson S. Polydopamine-melanin initiators for Surface-initiated ATRP. *Polymer* 2011;52:2141-9.
- [277] Bielawski CW, Grubbs RH. Living ring-opening metathesis polymerization. *Prog Polym Sci* 2007;32:1-29.
- [278] Wang D, Ye Q, Yu B, Zhou F. Towards chemically bonded p-n heterojunctions through surface initiated electrodeposition of p-type conducting polymer inside TiO₂ nanotubes. *J Mater Chem* 2010;20:6910-5.

