

Effect of glycerol, peanut oil and soybean lecithin contents on the properties of biodegradable film of improved cassava starches from Côte d'Ivoire

Adjouman Yao Désiré^{1,2,4*}, Nindjin Charlemagne^{1,2}, Konan Brou Roger¹,
Coulibaly Souleymane³, Amani N'Guessan Georges¹, Sindic Marianne⁴,
Tetchi Fabrice Achille¹

¹Departement des Sciences et Technologies des Aliments, Université Nangui Abrogoua, Abidjan, 02 B.P 801 Abidjan, Côte d'Ivoire

²Departement Sécurité des Aliments, Centre Suisse de Recherches Scientifiques en Côte d'Ivoire, Abidjan, 01 BP 1303 Abidjan, Côte d'Ivoire

³Station de Recherche Technologique du Centre National de Recherche Agronomique, Abidjan, 08 BP 881 Abidjan 08, Côte d'Ivoire

⁴Departement Qualité et Sécurité des Produits Agroalimentaires, Université de Liège, Gembloux Agro-Bio Tech, Gembloux, Passage des Déportés 5030, Belgium

Email addresses: desyadjouman@gmail.com; Charlemagne.nindjin@yahoo.fr; rogerkonan022002@yahoo.fr; coulisouley1@yahoo.fr; amanigeorges@yahoo.fr; marianne.sindic@ulg.ac.be; tetchifa@yahoo.fr

* Corresponding author: Adjouman Y.D., Doctor. E-mail address: desyadjouman@gmail.com

Abstract— Edible films have been successfully used in the food packaging industry for several decades. Today natural polysaccharides, including cassava starch, are increasingly being used in the production of such biodegradable edible films and food packaging. In Côte d'Ivoire, there are improved cassava varieties whose starches have not yet been tested in the production of biodegradable films. In this study, the optical and mechanical properties and the water solubility of starch-based composite films of four improved cassava varieties with added glycerol, peanut oil and soy lecithin were determined. Starch was obtained by cold water extraction from native cassava from the varieties Bocou 1, Bocou 2, Yavo and TMS. Films preparation was made by casting method with cassava, glycerol (25-30 %), peanut oil (5-10 %) and soybean lecithin (0-5 %). Increasing the glycerol content, increased L^* color value and elongation at break and decreased a^* , b^* , colour difference (ΔE^*_{ab}) and tensile strength of the composite films. Also, increasing the oil content from 5 to 10%, increased the opacity, b^* , ΔE^*_{ab} , water solubility, elongation at break but decreased L^* , a^* and tensile strength. Similarly, increasing the soy lecithin content from 0 to 5%, increased the opacity, L^* , b^* and ΔE^*_{ab} , but decreased a^* , of the starch-based composite films. The results suggest an ideal formulation of 4% starch/25% glycerol/5% oil/5% soy lecithin for a

film with optimum mechanical properties with low solubility.

Keywords— Biodegradable film, Cassava starch, Emulsified film, Mechanical properties, Starch-based film.

I. INTRODUCTION

Scientific literature now contains several studies aimed at improving the properties of materials already used or using new materials to produce packages having properties that may tend towards synthetics. Due to increasing pressure from society and legislation to reduce non-degradable synthetic packaging, research on the production of biodegradable alternatives prepared from natural biopolymers has been encouraged (Adjouman *et al.*, 2017). Biodegradable films are flexible and thin matrices used for coating and packaging in a diversity of product groups and industries. Main applications include food packaging, fruit coatings, pharmaceuticals and cosmetics. Films are predominantly made of natural biopolymers, such as polysaccharides, proteins and other abundant natural elements (Bergo *et al.*, 2010).

Starch is a polysaccharide composed of amylose, a linear polymer consisting of glucose with α (1-4) bonds, and amylopectin, a polymer with α (1-6) bonds. The amylose vs amylopectin ratio and, consequently, the form

and functionality vary between cultivars within and between species (Copeland *et al.*, 2009). Cassava (*Manihot esculenta* Crantz) roots are among the most important sources of starch worldwide. According to the Food and Agricultural Organisation (FAO), the global cassava production in 2015 was estimated at 281.1 million tonnes with 54 % produced in Africa (FAO, 2016). In Côte d'Ivoire cassava is the second major food crop after yam, with an estimated 5.1 million tonnes produced in 2015 (FAO, 2016). Unlike other starches, cassava starch allows obtaining transparent and flexible films (Vicentini and Cereda, 1999). However, for the production of edible films and optimised application in food technology plasticizers, hydrophobic agents and emulsifiers have to be added to the film composition (Bergoet *et al.*, 2010). Adding vegetable oils to hydrophilic films, for instance, reduces the water vapor barrier properties of films based on proteins (Fabraet *et al.*, 2009) and those based on polysaccharides (Koelsch and Labuza, 1992). Those emulsion-based films with enhanced physico-chemical and mechanical properties generally arise from oil droplets with small diameter, a high degree of homogeneity and highly stable film-forming emulsions (Nilsuwan *et al.*, 2016; Debeaufort *et al.*, 1995). For good dispersion/homogenization of the oil in the film-forming matrix, emulsifiers are therefore commonly added. They are nonpolar substances which bind to both water and oil, thus improving emulsification and increasing the stability of the emulsion. Furthermore, soybean lecithin incorporated into protein-based emulsified films has previously shown effective in stabilizing the emulsion film (Prodpran *et al.*, 2007). Lipid compounds are used to modulate the water barrier properties of films; however, in hydrophilic suspensions they adversely affect the mechanical and optical properties of the resulting films (Yang and Paulson, 2000). The most effective plasticizers are generally those whose structure resembles the structure of the polymer they plasticize. For starch-based films polyols such as sorbitol and glycerol are the commonly used plasticizers (Mali *et al.*, 2005). With increasing glycerol concentration, the breaking strain has shown to improve and the tensile strength to decrease (Alves *et al.*, 2007).

In Côte d'Ivoire, there are improved cassava varieties whose starches have not yet been tested in the production of biodegradable films. The aim of this study is to determine the effect of plasticizer, lipid and emulsifier contents on the mechanical properties, solubility, opacity and color parameters of films based on starch from improved cassava varieties grown in Côte d'Ivoire.

II. MATERIALS AND METHODS

Cassava natives starches from four improved varieties Bocou 1, Bocou 2, Yavo and TMS, belonging to Centre National de Recherche Agronomique in Côte d'Ivoire were used in this study. Cassava plants were harvested at maturity, 12 months after plantation. Glycerol (bidistilled, 99.5% purity) and soybean lecithin were purchased from VWR Prolabo Chemicals (Leuven, Belgium). The CORA brand peanut oil used in this study was purchased at a supermarket in Belgium.

2.1. Amylose content

The amylose content of the starch samples was determined by colorimetric reaction and subsequent measuring of the absorbance of the amylose-iodine blue complex formed (Morrison and Laignelet, 1983).

2.2. Starch paste clarity

The paste clarity of the starches was determined as previously described by Craig *et al.* (1989). Approximately 0.11 g of starch was weighed into quartz screw tubes. The mass was supplemented to 10 g with distilled water. The closed tube with the well homogenized content was left in boiling water bath at 100°C for 30 min with uniform stirring. The solution obtained was cooled and the paste clarity or percent transmittance (% T) was determined using a Shimadzu UV-2401-PC (Kyoto-Japan) spectrophotometer at 650 nm against a blank sample containing distilled water.

2.3. Film preparations and thickness measurements

Film preparation and thickness measurements were determined in accordance with previously described protocol (Adjouman *et al.*, 2017). The emulsified films were prepared in two steps. First, 4 g of cassava starch (w/w, starch) was mixed with glycerol (1–1.2 g) and with two thirds of distilled water, the final mixture being heated from 30°C to 75°C for 20 min. Peanut oil (0.2–0.4 g), soybean lecithin (30–60 mg) and distilled water (a third of the total mixture) (Table 1) was also heated together for 20 min from 30°C to 75°C. Both solutions were heated with constant stirring at 750 rpm/min. Thereafter, the solution of peanut oil, soybean lecithin and distilled water was homogenised at 24,000 rpm for 2 min using an Ultra-Turrax T25 basic (IKA Werke, Staufen /Germany). The homogenised solution was subsequently mixed with the starch and glycerol and then heated from 75°C to 95°C at 750 rpm stirring for 25 min. A 20 g aliquot of the final solution was transferred and spread with even thickness on the surface of a Petri dish (9 cm diameter) and oven-dried in a ventilated oven model (Memmert UF-110, Schwabach, Germany) at 35°C for 24 h. The dried films were removed and stored in a desiccator at 25°C for 48 h, before testing. The thickness of all films was determined using a hand micrometer (NSK, Japan) at 10 random positions of the films.

Table.1: Cassava starch-based film formulations

Formulation	Starch (g)	Oil 5 and 10% (g/g starch)	Glycerol 25 and 30% (g/g starch)	Lecithin 0 and 5% (mg/g oil)	Potassium sorbate (g)
F1: G25 H5 L0	4	0.2	1	0	0.2
F2: G25 H5 L5		0.2	1	30	
F3: G30 H5 L0		0.2	1.2	0	
F4: G30 H5 L5		0.2	1.2	30	
F5: G25 H10 L0		0.4	1	0	
F6: G25 H10 L5		0.4	1	60	
F7: FG30 H10 L0		0.4	1.2	0	
F8: G30 H10 L5		0.4	1.2	60	

G25 H5 L0 : 25 % glycerol/ 5 % oil/ 0% lecithin, G25 H5 L5 : 25 % glycerol/ 5 % oil/ 5% lecithin, G30 H5 L0 : 30 % glycerol/ 5 % oil/ 0% lecithin, G30 H5 L5 : 30 % glycerol/ 5 % oil/ 5% lecithin, G25 H10 L0 : 25 % glycerol/ 10% oil/ 0% lecithin, G25 H10 L5 : 25 % glycerol/ 10 % oil/ 5% lecithin, G30 H10 L0 : 30 % glycerol/ 10 % oil/ 0% lecithin, G30 H10 L5 : 30 % glycerol/ 10 % oil/ 5% lecithin.

2.4. Film water solubility

Film water solubility was determined as previously describe (López *et al.*, 2008). From each film pieces of 2 x 3 cm were cut and stored in a desiccator, containing silica gel beads, for 7 days. Pieces were weighed to the nearest 0.0001 g and placed into test beakers with 80 ml deionized water. The samples were left under constant stirring at 200 rpm for 1 h at room temperature. After 1 h, any remaining pieces of film were subsequently collected by filtration, dried again in an oven at 60°C to constant weight and the proportion of total soluble matter was calculated.

2.5. Film opacity

Film opacity was determined in accordance with previously described protocol (López *et al.*, 2008). Film samples were cut into rectangles of 1 x 3 cm and placed inside a spectrophotometer cell. The absorbance spectrum (400–700 nm) was recorded for each sample using a Shimadzu (UV-2401-PC Kyoto/Japon) spectrophotometer. Film opacity was determined by an integration procedure and expressed as absorbance units per nanometers (AU. nm).

2.6. Film color

The film L*, a* and b* color values were determined using a Miniscan XE HunterLab colorimeter (Virginia, USA) against the standard plate (L* = 93.5; a* = -0.61 and b* = 0.12). Color was measured on 8 x 8 cm segment of film. The total color difference (ΔE^*_{ab}) was calculated using the following equation 1:

$$\Delta E^*_{ab} = \sqrt{(L^*)^2 + (a^*)^2 + (b^*)^2} \quad (1)$$

Film specimens were pre-conditioned at 62% RH and 25°C for 72 h prior to taking color measurements.

2.7. Mechanical properties

Mechanical properties were studied using a TA.TX2 Stable Micro Systems Texture Analyzer. ASTM D882-02(2002), standard test method for tensile properties of thin plastic sheeting with some modifications was used. The films were cut into 25 mm wide and 80 mm long strips, using a scalpel and mounted between the grips (A/TG) of the texture analyser. The ends of the strips were mounted between cardboard grips. Strength resistance and deformation at break were recorded in tensile mode, during extension at 10 mm min⁻¹, with an initial 50-mm distance between the grips, until the specimens broke.

2.8. Statistical analysis

Using Statistica 7.1 software (Statistica), multivariate analyses of variance (MANOVA) was performed, to compare the means of the various properties of the film formulations (cassava variety and glycerol, peanut oil and soy lecithin added). Duncan's multiple range test at the 5% threshold, allowed locating the differences.

III. RESULTS AND DISCUSSION

3.1. Amylose content and paste clarity

Paste clarity and amylose content of cassava varieties used in this study are presented in Table 2. The highest value of amylose was obtained with the TMS variety, followed by the varieties Yavo, Bocou 2 and Bocou 1. In contrast, the clearest starch gel was obtained with the Bocou 1 variety, followed by Bocou 2, Yavo and TMS. Starches with low amylose content have high paste clarity. Amylose contents are known to influence clarity of starch pastes. High amylose content may result in more opaque starch pastes (Schmitz *et al.*, 2006).

Table.2: Amylose content and paste clarity of starches in cassava varieties

Cassava starch	Bocou 1	Bocou 2	Yavo	TMS
Amylose content* (%)	16.28 \pm 2.2 ^a	17.33 \pm 1.2 ^b	18.37 \pm 1.5 ^c	20.36 \pm 2.1 ^d
Starch paste clarity* (%) T)	71.02 \pm 3.2 ^a	69.77 \pm 2.5 ^b	61.33 \pm 2.1 ^c	48.86 \pm 1.3 ^d

% T : percent transmittance, *the means followed by a common letter are not significantly different by Duncan's multiple range test at $p < 0.05$.

3.2. Film water solubility

Glycerol, oil and lecithin added showed a significant difference in the water solubility of the starch films ($p < 0.05$). Increasing the concentration of glycerol from

25% to 30%, oil from 5% to 10% and lecithin from 0% to 5% resulted in increased water solubility of the composite films from all varieties (Table 3).

Table.3: Water solubility of cassava starch-based composite films

Formulation	Solubility (%)			
	Bocou 1*	Bocou 2*	Yavo*	TMS*
G25 H5 L0	47.14 \pm 1.48 ^a	42.88 \pm 1.87 ^a	40.49 \pm 2.75 ^a	37.15 \pm 1.76 ^a
G25 H5 L5	49.13 \pm 1.71 ^{ab}	43.90 \pm 1.00 ^{ab}	41.61 \pm 2.56 ^{ab}	39.61 \pm 0.58 ^{ab}
G25 H10 L0	62.75 \pm 3.36 ^d	61.67 \pm 3.36 ^d	58.32 \pm 2.43 ^d	52.99 \pm 2.43 ^d
G25 H10 L5	66.34 \pm 1.33 ^e	64.68 \pm 0.81 ^e	60.50 \pm 1.42 ^e	56.16 \pm 1.24 ^e
G30 H5 L0	51.85 \pm 1.24 ^b	45.95 \pm 1.82 ^b	45.01 \pm 2.18 ^b	44.35 \pm 2.14 ^b
G30 H5 L5	53.82 \pm 1.30 ^c	47.89 \pm 1.07 ^c	48.65 \pm 1.93 ^c	47.65 \pm 2.02 ^c
G30 H10 L0	73.19 \pm 2.84 ^f	69.53 \pm 0.74 ^f	62.32 \pm 0.56 ^f	59.65 \pm 0.82 ^f
G30 H10 L5	74.63 \pm 2.76 ^g	72.96 \pm 1.23 ^g	64.50 \pm 1.42 ^g	63.07 \pm 0.78 ^g

*The means followed by a common letter are not significantly different by Duncan's multiple range test at $p < 0.05$.

Increasing the glycerol content from 25% to 30% allowed an increase in the water solubility of the films of the starches of the four varieties of cassava. Such observations were made in previous studies on films based on bitter and soft cassava starch on the film-forming capacity of corn starch amended (Lopez *et al.*, 2008; Belibi, 2014). The demonstrated positive correlation between the solubility of the films and the plasticizer concentration may be due to the low molecular weight of the glycerol which enables it to be easily inserted between the polymer chains (Cuq *et al.*, 1997) and to the hydrophilic nature of glycerol (Lopez *et al.*, 2008). Furthermore, the increase in the glycerol concentration in biodegradable films was found to induce a marked decrease in the crystallinity of the starch films (Belibi, 2014). The less crystallites are formed in the films the more readily they will swell in the water and disintegrate.

Consequently, this will express in higher water solubility (Maizura *et al.*, 2007).

Increasing the oil content from 5% to 10% increased the water solubility of the starch films of all cassava varieties which is likely to be due to high degree of solubility of the fatty acids contained in the peanut oil. An increase in fat content increases solubility in water as long as the concentration of fatty acids is lower than the saturation level for an expected volume of water (Fakhouri *et al.*, 2009). Previous work on gelatin films with lauric, palmitic and stearic acids revealed indeed a positive correlation between water solubility and fatty acid content (Fakhouri *et al.*, 2003). Another study revealed that solubility of soy protein films showed a significant increase with the addition of lauric acid (Rhim *et al.*, 2002) supported by similar findings in wheat gluten films with added fatty acids (Gontard *et al.*, 1994).

The increase in soy lecithin content from 0 to 5% led to an increase in the water solubility of the starch films of all cassava varieties. It was hoped that the inclusion of compounds having hydrophobic characteristics (i.e. soy lecithin) could reduce the water solubility of cassava starch films; however, this behavior was not observed in this study. A study of edible composite films based on wheat gluten and lipids suggested that the increase in solubility due to addition of compounds with hydrophobic characteristics is related to the breakdown of the intermolecular bonds in the protein network and to the formation of weak interactions with hydrophobic substances (Gontard *et al.*, 1994). The subsequent increase in the solubility of cassava-based films when the concentration of soy lecithin is being raised is likely to be

related to the breakdown of the intermolecular bonds in the starch network.

3.3. Film opacity

The opacity values of the starch films of the different cassava varieties as a function of the different formulations are presented in Table 4. At a given concentration of glycerol addition of oil allowed an increase in the opacity of the films of cassava starches. Similarly, at a given concentration of glycerol and oil, addition of soy lecithin caused an increase in the opacity of cassava starch films. Highest values were found with films from TMS starch, followed by Yavo, Bocou 2 and Bocou 1. Added oil and lecithin and oil-lecithin combination showed significant differences in the opacity of the starch films of all cassava varieties ($p < 0.05$).

Table.4: Opacity of cassava starch-based composite films

Formulation	Opacity (AU nm ⁻¹)			
	Bocou 1*	Bocou 2*	Yavo*	TMS*
G25 H5 L0	110.64 ± 6.98 ^a	166.70 ± 15.05 ^a	169.21 ± 8.36 ^a	191.42 ± 4.61 ^a
G25 H5 L5	172.82 ± 6.40 ^c	257.27 ± 10.35 ^c	223.92 ± 3.41 ^c	251.42 ± 8.50 ^c
G25 H10 L0	155.65 ± 6.86 ^b	169.36 ± 3.47 ^b	208.15 ± 11.85 ^b	221.39 ± 3.30 ^b
G25 H10 L5	272.55 ± 11.19 ^d	322.62 ± 8.86 ^d	332.50 ± 12.09 ^d	348.66 ± 2.49 ^d
G30 H5 L0	132.82 ± 6.39 ^a	162.67 ± 7.02 ^a	181.56 ± 3.14 ^a	196.58 ± 1.77 ^a
G30 H5 L5	200.56 ± 5.13 ^c	264.62 ± 11.39 ^c	237.33 ± 8.49 ^c	259.06 ± 3.11 ^c
G30 H10 L0	171.47 ± 14.05 ^b	156.27 ± 7.15 ^b	209.09 ± 16.28 ^b	217.65 ± 6.71 ^b
G30 H10 L5	291.98 ± 5.07 ^d	299.29 ± 1.00 ^d	337.12 ± 17.07 ^d	348.57 ± 7.63 ^d

*The means followed by a common letter are not significantly different by Duncan's multiple range test at $p < 0.05$.

The increase in oil content from 5 to 10% allowed an increase in the opacity of the films of the starches of all cassava varieties, which is in line with previous study (Perez-Mateos *et al.*, 2009). Similar results were found in a study on the physical and barrier properties of composite films of apple pectin and manioc starch incorporated with *Laurus Nobilis* oil and oleic acid (Taqi *et al.*, 2014). The authors attributed this behaviour to the physical properties of oils at room temperature, which generally depends on the oil concentration in the film. The opacity of the films would therefore be linked to the oil droplets dispersed throughout the starch network and to the original color of the oil used. Similar observations were made previously on the whiteness of gelatin film color in relation to the sunflower oil dispersed in the emulsion (Perez-Mateos *et al.*, 2009) and opacity increase as a function of the fatty acid level in a film within a study on the effects of fatty acid addition to the properties of corn starch and gelatin films (Fakhouri *et al.*, 2009).

Increase in lecithin content from 0 to 5% allowed an increase in opacity of films from starches of all cassava varieties. We attribute this increase to original state of yellow soybean lecithin and a hydrophobic compound. Incorporation of the hydrophobic substances into the

hydrocolloid polymer HPMC matrix caused a decrease in the luminance of the films which resulted in an increase in their opacity in previous work (Quezada-Gallo *et al.*, 2000). An oil-soy lecithin combination also allowed an increase in opacity of starch films of four cassava varieties which seems to be accumulation of their individual effects. Opacity was more pronounced in TMS starch films than in starch films derived from the three other varieties used in this study and is related to the intrinsic characteristics of each starch variety specifically the starches paste clarity (Table 2).

3.4. Film color

The color parameters (Fig. 1) of the films were significantly influenced by the addition of glycerol, oil and lecithin ($p < 0.05$). Increasing the glycerol content, led to increased L* (Fig. 1a) and decreased a* (Fig. 1b), b* (Fig. 1c) and ΔE^*_{ab} (Fig. 1d), of starch films from four cassava varieties. Conversely, increasing the oil content, resulted in a decrease in L* and a*, and an increase in b* and ΔE^*_{ab} , of the starch films formulated using cassava varieties. Lecithin addition, resulted in an increased L*, b* and ΔE^*_{ab} , but decreased a*, of starch films of cassava varieties. The increase in b*, resulted in an increase in ΔE^*_{ab} of the resulting films.




Fig.1: Effect of glycerol, oil and soy lecithin on the colour parameters of films based on cassava starch, a) color parameter L^* , b) color parameter a^* , c) color parameter b^* , d) ΔE^* indexes

The study on HPMC films plasticized with 15 and 30% glycerol was showed a slight increase in L^* luminance but not a decrease in a^* , b^* and ΔE^*_{ab} indexes (Al Mahdi, 2006). However, our results concerning effect of oil on color parameters are consistent with studies on emulsified films based on gelatine of fish shell and palm oil (Tongnuanchan *et al.*, 2015) and on the stability of the emulsion and the properties of gelatin films affected by palm oil and emulsifiers (Nilsuwan *et al.* 2016). Previous studies in films with soy lecithin as emulsifier reported

highest b^* and ΔE^*_{ab} values compared with other emulsifiers (Nilsuwan *et al.*, 2016). Therefore, the colors of peanut oil and soy lecithin directly determined the color of the cassava starch films in this study.

3.5. Mechanical properties

Table 5 shows values of tensile strength and elongation at break of composite films based on cassava starch.

Table.5: Tensile strength and elongation at break values of cassava-based composite films

Formulations	Tensile Strength at break (MPa)				Elongation at break (%)			
	Bocou 1*	Bocou 2*	Yavo*	TMS*	Bocou 1*	Bocou 2*	Yavo*	TMS*
G25 H5 L0	2.82 ± 0.3 ^a	5.11 ± 1.2 ^a	5.26 ± 1.1 ^a	5.99 ± 1.6 ^a	15.08 ± 2.3 ^a	8.64 ± 1.8 ^a	8.20 ± 5.1 ^a	7.39 ± 1.7 ^a
G25 H5 L5	3.94 ± 1.6 ^b	6.22 ± 1.1 ^b	6.40 ± 1.2 ^b	7.92 ± 0.9 ^b	27.54 ± 3.2 ^b	18.17 ± 2.4 ^b	16.34 ± 2.1 ^b	17.82 ± 3.3 ^b

G25 H10 L0	0.96 ± 0.2 ^e	1.39 ± 0.3 ^e	1.26 ± 0.1 ^e	2.11 ± 0.5 ^e	73.66 ± 5.7 ^c	59.82 ± 3.4 ^e	60.12 ± 2.8 ^e	44.36 ± 4.7 ^e
G25 H10 L5	1.28 ± 0.1 ^e	1.49 ± 0.1 ^e	1.65 ± 0.2 ^e	2.23 ± 0.4 ^e	88.42 ± 1.6 ^c	73.28 ± 4.3 ^e	75.44 ± 4.8 ^e	54.23 ± 3.7 ^e
G30 H5 L0	2.08 ± 0.3 ^c	3.54 ± 0.4 ^c	3.90 ± 0.4 ^c	3.94 ± 0.4 ^c	35.77 ± 5.3 ^c	27.97 ± 2.6 ^c	21.47 ± 2.2 ^c	29.23 ± 6.0 ^c
G30 H5 L5	1.78 ± 0.6 ^d	2.51 ± 0.6 ^d	2.80 ± 0.6 ^d	2.98 ± 0.7 ^d	47.69 ± 4.3 ^d	35.16 ± 3.4 ^d	30.27 ± 4.2 ^d	30.91 ± 4.5 ^d
G30 H10 L0	0.71 ± 0.1 ^f	1.07 ± 0.3 ^f	1.09 ± 0.2 ^f	1.13 ± 0.1 ^f	95.44 ± 1.1 ^f	91.18 ± 2.8 ^f	87.41 ± 3.7 ^f	65.09 ± 2.1 ^f
G30 H10 L5	0.45 ± 0.1 ^g	0.69 ± 0.1 ^g	0.72 ± 0.1 ^g	0.89 ± 0.1 ^g	99.21 ± 1.4 ^g	99.50 ± 0.7 ^g	94.49 ± 3.8 ^g	85.56 ± 1.9 ^g

*The means followed by a common letter are not significantly different by Duncan's multiple range test at $p < 0.05$.

Increasing glycerol content from 25% to 30% resulted in a decrease in tensile strength at break and an increase in the elongation at break of films from cassava starches varieties. It has already been pointed out by several authors that increase in level of plasticizer such as glycerol in starch films leads to a decrease in tensile strength and an increase in elongation at break (Alves *et al.*, 2007; Bertuzzi *et al.*, 2012; Sanyang *et al.*, 2015). It has been shown that glycerol reduces the rigidity of the starch network, leading to a less orderly film structure and increasing the capacity of the polymer chain movement (Sothornvit and Krochta, 2005). These properties render glycerol a suitable plasticizer able to reduce intramolecular forces between starch chains and to promote hydrogen bond formation between plasticizer and starch molecules. An increase in elongation of films may be related to the fact that plasticizers decrease intermolecular bonds between amylose, amylopectin and amylopectin amylose phases of the starch and substituting them by hydrogen bonds formed between starch molecules and plasticizer (Sanyang *et al.*, 2015). Such perturbation and reconstruction of starch molecular chains reduces stiffness and promotes film flexibility by allowing greater mobility of the chain. Zavareze *et al.* (2012) have shown that elongation of the polymers depends on the mobility of their molecular chains.

Increasing oil content from 5% to 10% resulted in a decrease in tensile strength and an increase in elongation at break of starch films from all four cassava varieties. Similar results have been obtained on films based on cinnamon oil incorporated cassava starch (Souza *et al.* 2013) and a variety of other films with other polymers (Lopez *et al.*, 2008; Al Mahdi, 2006). The addition of lipids or oil to protein-based or polysaccharide-based films such as starch can reduce intermolecular interactions between polymer chains. The result is a decrease in stiffness with a concomitant increase in the extensibility/elasticity of the film obtained (Lopez *et al.*, 2008; Souza *et al.*, 2013). The combination of glycerol

and lecithin influenced tensile strength and elongation at break of films based on cassava starch ($p < 0.05$).

At 25% glycerol, addition of soybean lecithin resulted in an increase in tensile strength and an increase in elongation at break for all varieties; however, at 30% the addition resulted in decrease in tensile strength and increases an elongation at break of the starch-based films. This behavior observed at 30% glycerol when the soy lecithin is added could be due an apparent synergistic effect between glycerol and emulsifiers (Rodriguez *et al.*, 2006). This interaction means that the films with glycerol in the presence of an emulsifier mechanically behave in the form of films with a larger amount of plasticizer. At 25% glycerol, an increase in tensile strength was observed that is likely to be due to the good dispersion and distribution of the added oil in the film caused by the addition of 5% lecithin. It is well known that mechanical properties of emulsified films are improved when the hydrophobic compound is small and distributed more homogeneously (Debeaufort and Voilley, 1995). Resistance and elongation at break of starch films from four cassava vary between varieties. This difference in mechanical properties of films may be explained by the difference in amylose content of starches constituting these films. Indeed, as the amylose content of the starch increases at constant glycerol concentration, the tensile strength at break of the corresponding films increases while the elongation at break decreases (Alves *et al.*, 2007).

IV. CONCLUSION

Starches of improved cassava varieties in Côte d'Ivoire can be used in the production of biodegradable films with plasticizer, lipid and emulsifier. Effect of plasticizer, lipid and emulsifier concentration on films from four improved cassava varieties was evaluated. The increased levels of glycerol, oil and soybean lecithin influenced the properties of cassava-based starch films. The resultant films from improved cassava starch with glycerol, peanut

oil and soybean lecithin had satisfying mechanical properties and low water solubility. However, to further optimize other biodegradable compounds must be added to formulation.

ACKNOWLEDGMENTS

The authors would like to thank the Interprofessional Fund for Agricultural Research and Council (FIRCA) in Côte d'Ivoire, which has funded this study. They also would like to thank Marjorie Servais for establishing the film preparation method, Thomas Bertrand for all the technical support in the laboratory, Dr Jasmina Saric for revision of the manuscript and Dr. Hgazard who put at our disposal the cassava roots that were used for the study.

REFERENCES

- [1] Adjouman, Y. D., Nindjin, C., Tetchi, F. A., Dalcq, A. C., Amani, N. G. and Sindic, M. (2017). Water vapor permeability of edible films based on improved cassava (*Manihotesculenta* Crantz) native starches. *Journal of Food Processing and Technology*, 8, 665. doi: 10.4172/2157-7110.1000665
- [2] Al Mahdi, R. (2006). Mise au point et caractérisation de films comestibles à base de polysaccharides et de matières grasses (doctoral thesis). Institut National Polytechnique de Lorraine, Lorraine, France.
- [3] Alves, V. D., Mali, S., Beléia, A. and Grossmann, M. V. E. (2007). Effect of glycerol and amylose enrichment on cassava starch film properties. *Journal of Food Engineering*, 78, 941-946.
- [4] ASTM D882-02. (2002). *Standard test method for tensile properties of thin plastic sheeting*. Philadelphia : American Society for Testing and Materials.
- [5] Belibi, P. C. (2014). Development and characterization of biofilms based on cassava starch reinforced by bi and tri-dimensional mineral fillers. Thesis. Université de Haute Alsace, Mulhouse, France. 156p
- [6] Bergo, P., Sobral, P. J. A. and Prison, J. M. (2010). Effect of glycerol on physical properties of cassava starch films. *Journal of Food Processing and Preservation*, 34, 401-410.
- [7] Bertuzzi, M. A., Gottifredi, J. C. and Armada, M. (2012). Mechanical properties of a high amylose content corn starch based film, gelatinized at low temperature. *Brazilian Journal of Food Technology* (Campinas), 15, 219-227.
- [8] Copeland, L., Blazeka, J., Salmana, H. and Tanga, M. C. (2008). Form and functionality of starch. *Food Hydrocolloids*, 23(6), 1527-1534.
- [9] Craig, S. A. S., Maningat, C. C., Seib, P. A. and Hoseney, R. C. (1989). Starch paste clarity. *Cereal Chemistry*, 66, 173-182.
- [10] Cuq, B., Gontard, N., Cuq, J. L. and Guilbert, S. (1997). Selected functional properties of fish myofibrillar protein-based films as affected by hydrophilic plasticizers. *Journal of Agricultural and Food Chemistry*, 45, 622-626.
- [11] Debeaufort, F. and Voilley, A. (1995). Effect of surfactants and drying rate on barrier properties of emulsified edible films. *International Journal of Food Science and Technology*, 30, 183-190.
- [12] Fabra, M. J., Jiménez, A., Atarés L., Talens, P. and Chiralt, A. (2009). Effect of fatty acids and beeswax addition on properties of sodium caseinate dispersions and films. *Biomacromolecules*, 10, 1500-1507.
- [13] Fakhouri, F. M., Batista, J. A., Grosso, C. R. F. (2003). Efeito de coberturas comestíveis aplicada semgoiabasin natura (*Psidiumguajava* L.) I. Desenvolvimento e caracterização de filmes comestíveis de gelatina, triacetina e ácidos graxos. *Brazilian Journal of Food Technology*, 6, 301-308.
- [14] Fakhouri, F. M., Fontes, L. C. B., Innocentini-Mei, L. H. and Collares-Queiroz, F. P. (2009). Effect of fatty acid addition on the properties of biopolymer films based on lipophilic maize starch and gelatin. *Starch/Stärke*, 61, 528-536.
- [15] FAO. (2016). Food and Agriculture Organisation 359 of the United Nations. Food outlook : biannual report on global food markets. <http://www.fao.org/3/a-i6198e.pdf> Accessed 04.03.2017.
- [16] Gontard, N., Duchez, C., Cuq, J. L. and Guilbert, S. (1994). Edible composite films of wheat gluten and lipids water vapour permeability and other physical properties. *International Journal of Food Science and Technology*, 29, 39-50.
- [17] Koelsch, C. M. and Labuza, T. P. (1992). Functional, physical and morphological properties of methyl cellulose and fatty acid-based edible barriers. *LWT - Food Science and Technology*, 25, 404-411.
- [18] López, O. V., García, M. A. and Zaritzky, N. E. (2008). Film forming capacity of chemically modified corn starches. *Carbohydrate Polymers*, 73, 573-581.
- [19] Maizura, M., Fazilah, A., Norziah, M. H. and Karim, A. A. (2007). Antibacterial activity and mechanical properties of partially hydrolyzed sagostarch-alginate

- edible film containing lemongrass oil. *Journal of Food Science*, 72, C324-C330.
- [20] Mali, S., Sakanaka, L. S., Yamashita, F. and Grossmann, M. V. E. (2005). Water sorption and mechanical properties of cassava starch films and their relation to plasticizing effect. *Carbohydrate Polymers*, 60, 283-289.
- [21] Morrison, W. R. and Laignelet, B. (1983). An improved colorimetric procedure for determining apparent and total amylose in cereal and other starches. *Journal of Cereal Science*, 1, 9-20.
- [22] Nilsuwan, K., Benjakul, S. and Prodpran, T. (2016). Influence of palm oil and glycerol on properties of fish skin gelatin-based films. *Journal of Food Science and Technology*, 53, 2715-2724.
- [23] Pérez-Mateos, M., Montero, P. and Gómez-Guillén, M. C. (2009). Formulation and stability of biodegradable films made from cod gelatin and sunflower oil blends. *Food Hydrocolloids*, 23, 53-61.
- [24] Prodpran, T., Benjakul, S. and Artham, A. (2007). Properties and microstructure of protein based film from round scad (*Decapterus maruadsi*) muscle as affected by palm oil and chitosan incorporation. *International Journal of Biological Macromolecules*, 41, 605-614.
- [25] Quezada-Gallo, J. A., Debeaufort, F., Callegarin, F. and Voilley, A. (2000). Lipid hydrophobicity, physical state and distribution effects on the properties of emulsion based edible films. *Journal of Membrane Science*, 180, 37-46.
- [26] Rhim, J. W., Gennadios, A., Weller, C. L. and Hanna, M. A. (2002). Sodium dodecyl sulfate treatment improves properties of cast films from soy protein isolate. *Industrial Crops and Products*, 15, 199-205.
- [27] Rodríguez, M., Osés, J., Ziani, K. and Maté, J. I. (2006). Combined effect of plasticizers and surfactants on the physical properties of starch based edible films. *Food Research International*, 39, 840-846.
- [28] Sanyang, M. L., Sapuan, S. M., Jawaid, M., Ishak, M. R. and Sahari, J. (2015). Effect of plasticizer type and concentration on tensile, thermal and barrier properties of biodegradable films based on sugar palm (*Arenga pinnata*) starch. *Polymers*, 7, 1106-1124.
- [29] Schmitz, C. S., de Simas, K. N., Joao, J. J., de Mello Castanho Amboni, R. D. and Amante, E. R. (2006). Cassava starch functional properties by etherification-hydroxypropylation. *International Journal of Food Science and Technology*, 41, 681-687.
- [30] Sothornvit, R. and Krochta, J. M. (2005). Plasticizers in edible films and coatings. In J. H. Han (Ed.), *Innovations in food packaging* New York : Elsevier. pp. 403-433.
- [31] Souza, A. C., Goto G. E. O., Mainardi, J. A., Coelho, A. C. V. and Tadini, C. C. (2013). Cassava starch composite films incorporated with cinnamon essential oil : antimicrobial activity, microstructure, mechanical and barrier properties. *LWT-Food Science and Technology*, 54, 346-352.
- [32] Taqi, A., Mutihac, L. and Stamatin, I. (2014). Physical and barrier properties of apple pectin/cassava starch composite films incorporating *Laurus nobilis* L. oil and oleic acid. *Journal of Food Processing and Preservation*, 38, 1982-1993.
- [33] Tongnuanchan, P., Benjakul, S., Prodpran, T. and Nilsuwan, K. (2015). Emulsion film based on fish skin gelatin and palm oil physical, structural and thermal properties. *Food Hydrocolloids*, 48, 248-259.
- [34] Vicentini, N. M. and Cereda, M. P. (1999). Uso de filmes de fécula de mandioca empóscolheita de pepino (*Cucumis sativus* L.). *Brazilian Journal of Food Technology*, 12, 87-90.
- [35] Yang, L. and Paulson, A. T. (2000). Effects of lipids on mechanical and moisture barrier properties of edible gellan film. *Food Research International*, 33, 571-578.
- [36] Zavareze, E. R., Pinto, V. Z., Klein, B., El Halal, S. L. M., Elias, M. C., Prentice-Hernández, C. and Dias, A. R. G. (2012). Development of oxidised and heat-moisture treated potato starch film. *Food Chemistry*, 132, 344-350.