



Modified carbon xerogels as electrocatalyst supports for PEMFCs

Loïc NOUMBI¹, Ali HAIDER^{1,2}, Lucas ELVIRA², Sophie HERMANS², Nathalie JOB¹

¹University of Liège, Department of Chemical Engineering (B6a), Allée du 6 Août 11, 4000 Liège, Belgium.

²UCLouvain, IMCN Institute, Place Louis Pasteur 1 - bte L4.01.03, 1348 Louvain-la-Neuve, Belgium.

lnoumbi@uliege.be

Keywords: Fuel cells, Carbon xerogels, CVD-coating, Nitrogen-doping, Single atom, Rotating Disk Electrode, Accelerated Stress Tests

Proton Exchange Membrane Fuel Cells (PEMFCs) are devices able to generate electricity through a simple electrochemical reaction between dihydrogen and dioxygen, with numerous applications, mainly in the transportation sector. One of the major challenges in their deployment is to improve their lifetime. To achieve this, many studies focus on the electrodes, i.e. the catalytic layers, usually made of a carbon material onto which platinum or Pt-M (M being a transition metal) nanoparticles are supported [1].

Commercially, carbon black is the most used catalyst support, however carbon corrosion causes the platinum particles to detach and/or agglomerate, resulting in a decrease of the ElectroChemically active Surface Area (ECSA). To overcome this problem and improve the catalyst stability, previous studies focused on carbons with the most crystalline structure possible [2].

However, crystalline surfaces usually lead to more mobile Pt particles, resulting also in agglomeration and loss of ECSA, thus making it necessary to better anchor the metal particles onto the support. The main goal of this work is therefore to improve the stability and durability of the carbon material used in PEMFCs. To achieve this, carbon xerogels were synthesized and used as main support. Their advantage is their tuneable pore texture from small mesopores to large macropores, enabling to manage mass transport within the electrode [3]; however as disordered carbons, they are prone to oxidation upon cell operation.

To tackle that issue, a more crystalline layer of carbon was firstly deposited on their surface using the Chemical Vapor Deposition (CVD) method. Secondly, functionalization processes were applied to these carbons (CVD-coated or not) using nitrogen-rich compounds to improve the anchoring of metal particles [4], that were deposited subsequently onto the carbon surface. In order to avoid the use of platinum, efforts are consented in parallel to synthesize iron-nitrogen doped carbon, structures that are well known in the field of single atom catalysts but remain to be fully exploited in PEMFCs [5].

To correlate the carbon properties with the catalyst stability, physicochemical properties and electrochemical performances were studied before and after ageing using Accelerated Stress Tests (ASTs) on Rotating Disk Electrode (RDE) configuration. In a further step, electrochemical characterization and ASTs will be performed in complete Membrane-Electrodes Assemblies with the most promising catalysts.

Acknowledgements

The authors would like to thank the F.R.S-FNRS and TiNTHyN for providing funding via a PDR project (Convention T.0166.24).

REFERENCES

1. O. A. Baturina, A. E. Smirnova, In: *New and Future Developments in Catalysis*, 69–97 (2013)
2. L. Castanheira *et al.* Carbon Corrosion in Proton-Exchange Membrane Fuel Cells: From Model Experiments to Real-Life Operation in Membrane Electrode Assemblies, *ACS Catalysis*, **4**, 2258–2267 (2014)
3. N. Job *et al.* Carbon xerogels as catalyst supports for PEM fuel cell cathode, *Energy Conversion and Management*, **49**, 2461–2470 (2008)
4. S. Carlier *et al.* Ru on N-doped carbon supports for the direct hydrogenation of cellobiose into sorbitol, *Applied Catalysis B : Environmental*, **282**, 119515 (2021)
5. T. Asset, P. Atanassov. Iron-Nitrogen-Carbon Catalysts for Proton Exchange Membrane Fuel Cells, *Joule*, **4**, 33-44 (2020)